

**RUST-OLEUM®**  
INDUSTRIAL



**DACFILL® HZ**

## Durable waterproofing for horizontal roofs



- Quick drying 100% watertight coating
- Resistant to UV radiation, acid rain, heat, frost and pollution
- White colour reflects most sunlight
- Non-flammable and self-extinguishing
- Seamless elastic finish lasts for years

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU



# DACFILL® HZ

## DESCRIPTION

Quick drying watertight water-based liquid membrane for roofs. Forms a lasting elastic coat without joint or seams on horizontal roofs.

## RECOMMENDED USE

Waterproofing protection of flat roofs. Also applicable in situations where quick water resistance or recoatability is required. Builds an abrasion resistant rubberlike coat without joints or seams, which is hardly flammable and self-extinguishing.

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,25
Gloss Level:	Matt
Solids Content in weight:	62%
Solids content in volume:	51%
Water Vapour Permeability:	$\mu = 1934 (2 \times 500 \text{ g/m}^2)$
Mixing Ratio:	Base : Activator = 19.2 : 0.8 (Weight)

## DRY TIMES BY 20° C/RH 50%

Touch dry:	1,5 hours
Dry to handle:	1,5 hours
Dry to recoat:	12 hours
Fully cured:	1 week
Pot Life:	18 hours

## RECOMMENDED WET FILM THICKNESS

1200 micron per coat (cons.: 1,5 kg/m<sup>2</sup>)

## RECOMMENDED DRY FILM THICKNESS

600 micron per coat (cons.: 1,5 kg/m<sup>2</sup>)

## THEORETICAL CONSUMPTION

Per coat: 1 - 1,5 kg/m<sup>2</sup> (depending of the substrate). To be applied in 2 coats.

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

The substrate must be well clean and dry, free from flakes, gravel, dust and dirt. Fill up joints with Elastofill, bridge active cracks with "Dacfill bridging mesh" and apply one of the following priming coats:

- On porous concrete, hard PVC and polyester: Primer 44HS
- On very smooth concrete: Noxyde diluted with 25% volume water
- On iron and steel: undiluted Noxyde

Roofing or bituminous materials over 1 year old can be coated directly with Dacfill HZ depending on its condition. To ensure optimal adhesion it is recommended to fixate the substrate with Parafix. Zinc, galvanised steel, copper, lead and aluminium can be recoated with Dacfill HZ, if required, after degreasing and slight sanding.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use. Add B-component to the A-component while stirring mechanically. It is advised to use the mixed material during the same day. Unroll the Dacfill-mesh on the dry and clean substrate and fix it to the substrate with a first coat of Dacfill HZ (1 - 1,5 kg/m<sup>2</sup>) by roller. Mesh overlappings must be at least 5 cm. After drying, a second coat of Dacfill HZ is to be applied by roller or by airless so that the structure of the mesh is not visible anymore.

## APPLICATION CONDITIONS

Dry weather: enough air ventilation (light breeze) or sunny conditions. Minimum Temperature: 5°C. Max. Relative humidity: 85%.

## APPLICATION & THINNING: BRUSH

Square brush. Do not dilute.

## APPLICATION & THINNING: ROLLER

Roller with long hairs (long nap). Do not dilute.

## APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 18 - 23 / Pressure: 220 bars. Do not dilute.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not advised

## CLEANING OF EQUIPMENT / SPILLS

Water

## REMARKS

Dacfill-mesh must be used on every roof with a slope < 5%, in case of water stagnation and when movements of the substrates can be expected or can be feared (for more information about the application of the Dacfill-mesh, please consult our Technical Service). For substrates other than those mentioned above contact Technical Service Do NOT apply on TPO's (Thermoplastic Olefins i.e. Derbigum)

Drying times depend strongly on temperature, relative humidity and air movement. Surface drying (1 kg/m<sup>2</sup>): 30 minutes (high t° / low R.H.) , 6 hours (low t° / high R.H. / no wind) Shore hardness A (ASTM D 2240): 75

## SAFETY DATA

VOC level:	55 g/l
VOC readymix:	55 g/l
VOC category:	A/j
VOC limit:	140 g/l
Grenelle:	Exterior
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 20/03/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu