

RUST-OLEUM®
— INDUSTRIAL —



DACFILL PU BASECOAT

Seamless waterproofing membrane for roofs



- Easy to apply and detail
- Wet-on-wet application
- Compatible with most existing roof membranes
- Permanent elastomeric and seamless
- Excellent resistance to ponded water

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

DACFILL PU BASECOAT

BESKRIVELSE

Dacfill PU embedment coat is a low odour, cold applied single pack, ultra high solids moisture activated elastomeric urethane coating.

ANBEFALET BRUG

For application in conjunction with Dacfill Fleece glass fibre reinforcement as the basecoat in Dacfill PU roof waterproofing membrane systems. A high build, heavy duty coating, almost free from solvent odour that provides durable, long term protection for roofs. To be used as a fully reinforced weatherproofing system.

ANBEFALET SYSTEM

3388 Metal Primer
3377 Binder Sealer
Dacfill PU Base coat
Dacfill Fleece
Dacfill PU Top coat

TEKNISK DATA

Tæthed: 1.45
Tørstofindhold i volumen: 87%

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør: 4 hours
Håndteringstør: 24 hours
Genbehandlingstør: 24 hours

ANBEFALET TØRFILMTYKKELSE

0.9-1.1 mm including reinforcement

TEORETISK FORBRUG

0.8-1.0 m² per litre

PRAKTISK FORBRUG

Dependent on surface profile

FORBEHANDLING AF OVERFLADEN

Inspect all surfaces to assess soundness of existing substrates or coatings. Where necessary prepare test areas. Roof surfaces must be clean, dry and free from all loose debris and be carried out before application of the coating. All areas of fungal growth, moss etc should be treated with AMW Fungicidal Wash and neutralised residues removed. Apply over Dacfill Fleece reinforced Base Coat (where necessary). Priming, where necessary should be carried out using suitable compatible materials. Contact Rust-Oleum Technical Department for further advice.

BRUGSANVISNING

Brush or roller. Apply at the prescribed system coverage rate to properly prepared areas. Immediately lay Dacfill glass fibre matting into applied coating, ensuring a minimum overlap of 50mm between sheets. Roll or tamp the surfaces to ensure full integration and saturation of the matting is achieved. Allow Base Coat to become firm before applying Dacfill PU Top Coat(s).

ANVENDELSESBETINGELSER

Do not apply if rain is imminent.

PÅFØRING OG FORTYNDING: PENSEL

Do not thin

PAFØRING OG FORTYNDING: RULLE

Do not thin

RENGØRING AF Udstyr/SPILD

Thinner 150

BEMÆRKNINGER

Overcoating must be carried out within the timescale overleaf otherwise further preparation may be necessary.

For any information regarding options of guarantee with this system, please contact Technical Service.

SIKKERHEDSDATA

VOC-niveau: <175g/l
VOC-kategori: Cat A/i.
VOC-grænse: EU limit 500g/l

HOLDBARHED

12 months from manufacturing date in unopened containers.

Udstedelsesdato: 22/11/2023

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu