

RUST-OLEUM®
INDUSTRIAL



DACFILL® PU TOPCOAT



Seamless waterproofing membrane for roofs

- Easy to apply and detail
- Compatible with most existing roof membranes
- Permanent elastomeric and seamless
- Excellent resistance to ponded water
- Fibre reinforced for maximum film strength

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

DACFILL® PU TOPCOAT

ОПИСАНИЕ

Dacfill PU top coat is a low odour, cold applied single pack, ultra high solids moisture activated elastomeric urethane coating.

ПРЕПОРЪЧАНА УПОТРЕБА

For application as the top coat in Dacfill PU roof waterproofing membrane systems. A high build, heavy duty coating, almost free from solvent odour that provides durable, long term protection for roofs. To be used as a fully reinforced weatherproofing system.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

3388 Metal Primer
3377 Binder Sealer
Dacfill PU Embedment coat
Dacfill Fleece
Dacfill PU Top coat
Dacfill PU Fibres

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³): 1.45
Съдържание на твърди вещества в обема: 87%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир: 4 hours
Сух за употреба: 24 hours
Готов за повторно нанасяне: min. 24 hours, max. 7 days

СУХ СЛОЙ

0.45-0.7 mm per coat (depending on the system)

РАЗХОДНА НОРМА

1-2m² per litre per coat

КОНСУМАЦИЯ

Dependent on surface profile, reinforcement where applicable etc.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

Inspect all surfaces to assess soundness of existing substrates or coatings. Where necessary prepare test areas. Roof surfaces must be clean, dry and free from all loose debris and be carried out before application of the coating. All areas of fungal growth, moss etc should be treated with AMW Fungicidal Wash and neutralised residues removed. Apply over Dacfill Fleece reinforced Embedment Coat (where necessary). Priming, where necessary should be carried out using suitable compatible materials. Contact Rust-Oleum Technical Department for further advice.

НАЧИН НА УПОТРЕБА

Brush or roller. May be used as the carrier for Dacfill glass fibre reinforcement matting on localised repairs.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply if rain is imminent.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Do not thin

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Do not thin

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Thinner 150

ЗАБЕЛЕЖКИ

Overcoating must be carried out within the timescale overleaf otherwise further preparation may be necessary.

For any information regarding options of guarantee with this system, please contact Technical Service.

This product does contain isocyanates. Users must follow mandatory training to comply with EU 2020/1149 Restriction 74.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС: <175g/l
Категория ЛОС: Cat A/i
Ограничение за ЛОС: EU limit 500 g/l

СРОК НА ГОДНОСТ

12 months from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu