

RUST-OLEUM®
— INDUSTRIAL —



EPOXYSHIELD® CONCRETE REPAIR MORTAR

For leveling and repairing cracks and holes



- Traffic allowed after 24 hours
- Recoatable after 48 hours
- 10 kg (1-component) – 0.4 m²
- Sandable to a smooth finish

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

EPOXYSHIELD® CONCRETE REPAIR MORTAR

DESCRIPTION

Powdered repair product on cement base and resins for inside and outside use. For leveling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

DOPORUČENÉ POUŽITÍ

For levelling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

TECHNICAL DATA

Hustota (g/cm³): 1,6
Míchací poměr: Powder : Water = 5kg : 1L

DRY TIMES BY 20° C/RH 50%

Suchý nátěr: 2 days
Plně vytvrzené: 1 month

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

2 cm (cons.: 25 kg/m²)

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

2 cm (cons.: 25 kg/m²)

TEORETICKÁ SPOTŘEBA

Maximum 0,4 m² per 10 kg (film thickness 2 cm).

PŘÍPRAVA POVRCHU

On bare substrate: clean with steel brush or sand blaster. The substrate must be solid and free from dust, oil and grease. Porous substrates must be moistened first. Metal parts are to be treated with an anti-rust primer (Combiprimer 3369/3380 or Hard Hat 2169/2182).

PODMÍNKY POUŽITÍ

Apply at a temperature of min. 5°C.

APLIKACE A ŘEDĚNÍ: HRÁBĚ/HADICE

Mixing & Thinning: Mixing ratio: Approximately 5 parts of powder to 1 part of water (2 litres of water for the entire 10 KG). Fill the container with the water. Add the dry mortar to the water whilst stirring. Mix water and powder thoroughly to a thick smooth, lump-free substance. Add some water to your liking if the mortar is too dry.

Application: Apply the product with the included trowel or spatula up to a maximum layer thickness of 2 cm. Wet the trowel to smooth out any trowel marks or irregularities. After 48 hours the surface can be sanded using a rough sandpaper (P120) to obtain a smooth end result.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water

POZNÁMKY

The mortar can now be over coated with EpoxyShield® coatings or other non-alkyd paints like Epoxies, Acrylics, etc.

If thicker layers are necessary (> 2 cm) the mortar can be mixed with kiln dried quartz sand. Mixing ratio: 1 volume part mortar plus 0,3 to 0,5 volume parts of kiln dried quartz sand (0 - 4 mm).

SAFETY DATA

Úroveň těkavých organických látek: 0 g/l
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 10/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu