

**RUST-OLEUM®**  
INDUSTRIAL



## EPOXYSHIELD® SEALER



# Water based, single pack dust-proofer

- Single pack, easy to apply
- Non yellowing clear finish (gloss)
- Touch dry after just 1 hour
- Ideal primer for EpoxyShield® ULTRA coatings

KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# EPOXYSHIELD® SEALER

## BESKRIVNING

One component, water-based, concrete sealer based on a vinyl acrylic binder. It reduces dust production and simplifies cleaning.

## REKOMMENDERAD ANVÄNDNING

When EpoxyShield® Sealer is used as a finish, apply 2 coats. EpoxyShield® Sealer can also be used as a sealer/impregnation primer for EpoxyShield® 5200 ULTRA. Apply the sealer on bare and clean concrete floors.

## TEKNISK DATA

Densitet:	1,02
Glansnivå:	Glans
Torrsubstansvolym:	30%

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	approximately 1 hour
Torktid:	after 6 hours
Fullt härdad:	8-12 hours

## ÅTGÅNG

Maximum 10 m<sup>2</sup> per litre.

## ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FÖRBEREDELSE

Apply the product only on fully clean and dry concrete surfaces. Do not apply on smooth or very dense concrete or concrete which contains curing compound. Remove all oil, grease and other dirt using EpoxyShield® Cleaner/Degreaser 2901. New concrete has to cure for minimal 30 days. All laitance, loose or unsound concrete should preferably be removed by blasting, cutting or etching with RUST-OLEUM Surfa-Etch 108 Etching Solution. Repair all holes and cracks with EpoxyShield® concrete repair products. Very dense and smooth concrete should first be abrasive blasted (or etching). During application the substrate should be clean and dry.

## APPLICERING

Mix the product prior for use.

## APPLICERINGSFÖRHÅLLANDEN

Temperature of air, substrate and coating material between 10 and 35°C, relative humidity below 85%. The substrate temperature must be at least 3°C above dew point. Ventilate well during and after application.

## REDSKAP

Product is ready for use. Thinning is not necessary.

## APPLICERING OCH SPÄDNING: ROLLER

Product is ready for use. Thinning is not necessary.

## RENGÖRING AV REDSKAP/SPILL

Direct after application with water and soap.

## INFORMATION

Walkable: after 8 - 12 hours

## SÄKERHETSDATA

VOC-nivå:	77 g/l
VOC färdigmix:	77 g/l
VOC-kategori:	A/i
VOC-gräns:	140 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 13/05/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)