

RUST-OLEUM®
INDUSTRIAL



FASSICLOR® SWIMMING POOL PAINT

Decorative paint for swimming pools or fountains

- Decoration or renovation of swimming pools
- Alkali and acid resistant
- Excellent flow; easy to apply
- UV-stable satin gloss finish
- Single pack paint

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

FASSICLOR® SWIMMING POOL PAINT

DESCRIPTION

Single pack colourfast decorative paint for decoration or renovation of concrete swimming pools or fountains.

RECOMMENDED USE

Decorative painting of swimming pools or fountains made of concrete.

TECHNICAL DATA

Density (g/cm ³):	1,25
Gloss Level:	Satin
Solids Content in weight:	53%
Solids content in volume:	31%

DRY TIMES BY 20° C/RH 50%

Touch dry:	1,5 hours
Dry to handle:	3 hours
Dry to recoat:	24 hours
Fully cured:	12 days

RECOMMENDED WET FILM THICKNESS

165 µm

RECOMMENDED DRY FILM THICKNESS

50 µm

THEORETICAL CONSUMPTION

2 coats of ± 6 m²/l per coat

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Apply without priming coat on old chlorinated rubber paint (after cleaning) or on a hardened and dry concrete substrate (maximum humidity degree 5%). Attention: since Fassiclor is not a waterproofing product, the concrete substrate must be waterproof!

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.

APPLICATION & THINNING: BRUSH

If necessary, dilute slightly with Thinner 22.

APPLICATION & THINNING: ROLLER

Apply the first coat with brush by preference, if necessary dilute slightly with Thinner 22.

APPLICATION & THINNING: AIRLESS SPRAY

Dilute with ± 10 – 20% volume Thinner 22. Nozzle: 018 / Pressure: 200 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

If necessary, dilute slightly with Thinner 22.

CLEANING OF EQUIPMENT / SPILLS

Thinner 22

REMARKS

When using in indoor swimming pools, especially during airless spraying, it is advisable to wear a mask due to limited ventilation. Swimming pools and other under water applications have to dry/cure for minimal 14 days before they can be immersed with water. Early contact with water can cause premature fading, chalking and blistering. Old coatings: only apply on perfectly sound similar and compatible paints (test in case of doubt). Building design of pool must be in accordance with specific construction rules. Water chemistry balance must be respected (Ph, water hardness, alkalinity etc). Any specific water treatment (salt, ozone, etc.) must be checked to avoid impact on coating system. A swimming pool specialist should be consulted for further information before applying any coating system.

SAFETY DATA

VOC level:	580 g/l
VOC readymix:	640 g/l
VOC category:	Exempt
VOC limit:	Exempt
Grenelle:	Exterior
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 20/03/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu