

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## FASSILUX<sup>®</sup> GLOSS

### Solvent based high gloss enamel

- Simple and fast application
- Excellent flow
- Excellent scratch and wear resistance
- Good outdoor durability, weatherproof
- Quick drying

# FASSILUX® GLOSS

## DESCRIPTION

Solvent based high gloss enamel based on alkyd resins.

## RECOMMENDED USE

Topcoat for interior and exterior woodwork.

## RECOMMENDED SYSTEM

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,17 - 1,20
Gloss Level:	Gloss
Solids Content in weight:	77 - 79 %
Solids content in volume:	70 - 72 %

## DRY TIMES BY 20° C/RH 50%

Touch dry:	3 hours
Dry to handle:	4 hours
Dry to recoat:	24 hours
Fully cured:	1 week

## RECOMMENDED WET FILM THICKNESS

50 µm

## RECOMMENDED DRY FILM THICKNESS

35 µm

## THEORETICAL CONSUMPTION

20 m<sup>2</sup>/l per coat

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

For top quality work, apply two coats of Fassiprim, sanding between each coat carefully. In some cases, the 2 coats of Fassiprim can be replaced by 1 thick coat of Fassicoat. For exterior works, it is advisable to apply an impregnating coat of FassiForce on bare or stripped wood, or on low grade wood. Do not use Fassicoat on metallic substrate; in this situation, use a tintable Rust-Oleum anticorrosion primer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti's, with Zinsser primer Cover-Stain.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Apply in a dry and well-ventilated area. Temperature minimum 10°C. Relative humidity maximum 80%.

## APPLICATION & THINNING: BRUSH

Do not dilute

## APPLICATION & THINNING: ROLLER

Do not dilute

## APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 09 - 013 / Pressure: 180 bars. Do not dilute.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Do not dilute

## CLEANING OF EQUIPMENT / SPILLS

White spirit or Thinner 22.

## REMARKS

Apply Fassilux in thin layers.

## SAFETY DATA

VOC level:	300
VOC category:	A/d
VOC limit:	300 g/l (2010)
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5° and 35°C.

Date issued: 07/02/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu