

RUST-OLEUM®
INDUSTRIAL



9740 FAST BALCONY SYSTEM TOPCOAT

**Sealercoat based on a
polyaspartic resin system**



- Low odour formula
- Walkable after 60-90 mins
- 1-2 coat fully reinforced waterproofing membrane
- Easy to apply and detail
- Low textured, slip resistant finish

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

9740 FAST BALCONY SYSTEM TOPCOAT

DESCRIPTION

A low solvent odour, flexible top coat for use within the Rust-Oleum Fast Balcony System to encapsulate anti-slip aggregates and provide a durable, full gloss finish.

DOPORUČENÉ POUŽITÍ

The topcoat of the Fast Balcony System system is specifically intended for use on medium to high wear areas on communal balconies and walkways

DOPORUČENÝ SYSTÉM

Fast Balcony System Grit Coat in combination with Dacfill Fleece

Aluminum Oxide Grits

Fast Balcony System Top Coat

TECHNICAL DATA

Hustota (g/cm³): 1,1

Úroveň lesku při 60°: Gloss

Úroveň lesku při 85°: Gloss

Obsah pevných láték v objemu: 85%

Michačí poměr: Stir base to even consistency then add one complete unit of activator. Mix well to uniform blend, ensuring base material is worked away from sides and bottom of container.

DRY TIMES BY 20° C/RH 50%

Dotykem suché: 1 hour

Suché na manipulaci: 1,5 hour

Suchý náter: min 1,5 hr, max 3 days

Život v hrnci: 15 minutes at 20°C

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

170 microns

TEORETICKÁ SPOTŘEBA

4-5m²/liter achieves 170-210 microns dry

PRAKTIČKÁ SPOTŘEBA

Typically 4-6m²/liter. Coverage rate may vary depending on size, type and spreading rate of aluminium oxide grits.

PŘÍPRAVA POVRCHU

Apply the aggregate in the wet paint film

NÁVOD K POUŽITÍ

Temperatures above 25°C and very high humidity will reduce pot life. Application at very low temperatures will significantly retard cure. Do not apply when rain is imminent.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Do not thin

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply one coat by roller to give an even spread, ensuring good cover on entire surface.

Apply mixed material as soon as possible to maintain workability. Do not thin.

ČIŠTĚní ZAŘÍZENÍ / ROZLITÍ

Thinner 150

POZNÁMKY

Do not apply to inadequately prepared or unsound surfaces. This product should only be applied by Rust-Oleum approved contractors (further details on request). Substrates must be dry during application otherwise curing defects will occur.

SAFETY DATA

Úroveň těkavých organických

látok: <200 g/l

Kategorie VOC: cat A/j

Limitní hodnota VOC: 500 g/l

DOBA POUŽITELNOSTI

12 months from date of production in unopened cans. If stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5°C and 35°C.

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shandon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu