

RUST-OLEUM®
— INDUSTRIAL —



9740 FAST BALCONY SYSTEM TOPCOAT

Sealercoat based on a polyaspartic resin system



- Low odour formula
- Walkable after 60-90 mins
- 1-2 coat fully reinforced waterproofing membrane
- Easy to apply and detail
- Low textured, slip resistant finish

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

9740 FAST BALCONY SYSTEM TOPCOAT

BESKRIVELSE

A low solvent odour, flexible top coat for use within the Rust-Oleum Fast Balcony System to encapsulate anti-slip aggregates and provide a durable, full gloss finish.

ANBEFALET BRUG

The topcoat of the Fast Balcony System system is specifically intended for use on medium to high wear areas on communal balconies and walkways

ANBEFALET SYSTEM

Fast Balcony System Grit Coat in combination with Dacfill Fleece
Aluminum Oxide Grits
Fast Balcony System Top Coat

TEKNISK DATA

Tæthed:	1,1
Glansgrad ved 60°:	Gloss
Glansgrad ved 85°:	Gloss
Tørstofindhold i volumen:	85%
Blandingsforhold:	Stir base to even consistency then add one complete unit of activator.Mix well to uniform blend, ensuring base material is worked away from sides and bottom of container.

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	1 hour
Håndteringstør:	1,5 hour
Genbehandlingstør:	min 1,5 hr, max 3 days
Brugstid:	15 minutes at 20°C

ANBEFALET VÅDFILMTYKKELSE

170 microns

TEORETISK FORBRUG

4-5m²/liter achieves 170-210 microns dry

PRAKTISK FORBRUG

Typically 4-6m²/liter. Coverage rate may vary depending on size, type and spreading rate of aluminium oxide grits.

FORBEHANDLING AF OVERFLADEN

Apply the aggregate in the wet paint film

BRUGSANVISNING

Temperatures above 25°C and very high humidity will reduce pot life. Application at very low temperatures will significantly retard cure. Do not apply when rain is imminent.

PÅFØRING OG FORTYNDING: PENSEL

Do not thin

PÅFØRING OG FORTYNDING: RULLE

Apply one coat by roller to give an even spread, ensuring good cover on entire surface.
Apply mixed material as soon as possible to maintain workability. Do not thin.

RENGØRING AF UDSKYR/SPILD

Thinner 150

BEMÆRKNINGER

Do not apply to inadequately prepared or unsound surfaces. This product should only be applied by Rust-Oleum approved contractors (further details on request). Substrates must be dry during application otherwise curing defects will occur.

SIKKERHEDSDATA

VOC-niveau:	<200 g/l
VOC-kategori:	cat A/j
VOC-grænse:	500 g/l

HOLDBARHED

12 months from date of production in unopened cans. If stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5°C and 35°C.

Udstedelsesdato: 10/03/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu