

RUST-OLEUM®
INDUSTRIAL



3377 FBS/DPU BINDER SEALER

2K moisture curing polyurethane binder sealer



- Moisture curing binder sealer
- Use on a wide range of substrates
- Fast drying

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

3377 FBS/DPU BINDER SEALER

BESKRIVELSE

An all-aliphatic stabilising sealer and primer for use on a wide range of substrates such as concrete, asphalt, bitumen, felt, asbestos, plaster, render, etc.

ANBEFALET BRUG

An all-aliphatic stabilising sealer and primer for use on a wide range of substrates such as concrete, asphalt, bitumen, felt, asbestos, plaster, render, etc.

TEKNISK DATA

Tæthed: 1.1
Tørstofindhold i volumen: 68%
Blandingsforhold: 10:1 by volume Base:Activator

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør: 2 hours
Håndteringstør: 3 hours
Genbehandlingstør: Min 3 hours, max 48 hours

ANBEFALET TØRFILMTYKKELSE

70 microns

TEORETISK FORBRUG

Up to 12m²/litre/coat (low porosity substrates)

PRAKTISK FORBRUG

Varies according to porosity, surface profile, etc – typically 10m²/litre on porous and/or rough surfaces.

FORBEHANDLING AF OVERFLADEN

All surfaces to be treated should be clean, sound, dry (preferably less than 5.5 on the Protimeter concrete moisture scale), sound and free from laitance, dirt, dust and other contaminants (note: deeply contaminated substrates may require special treatment). Rake out loose and friable materials and make good with a suitable proprietary filler or repair compound. Bare concrete surfaces should be suitably prepared (e.g. abrasive blast, disc grinding, scabbling, sanding, etc.) to give a clean, open textured surface. All previously coated areas should be carefully inspected. Where necessary, any residual coatings should be completely removed to promote good substrate adhesion. Any firmly adhering coatings must be inspected and application tests carried out to verify proposed system adhesion. If adhesion is unsatisfactory complete removal of coatings may be required unless an alternative spot primer can be used. Treat any areas of moss or fungal attack with AMW Fungicidal wash.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

Below 8°C cure times will be significantly extended. At very low temperatures, cure may be curtailed. Product will only tolerate a dampness of surface - not running water.

PÅFØRING OG FORTYNDING: PENSEL

Do not thin

PÅFØRING OG FORTYNDING: RULLE

Do not thin

RENGØRING AF UDSKYR/SPILD

Clean with Thinner 150

SIKKERHEDSDATA

VOC-niveau: max. 350 g/l
VOC-kategori: Cat IIA/h.
VOC-grænse: EU limit 750g/l (2007), 750g (2010)
Bemærkninger om sikkerhed: When airless spraying operatives must wear self contained breathing apparatus (contains isocyanates).

HOLDBARHED

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5°C and 35°C.

Udstedelsesdato: 03/01/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu