

RUST-OLEUM®
— INDUSTRIAL —

3388 FBS METAL PRIMER

Low odour, high performance 2 pack epoxy primer

Very low odour

For manually cleaned steel

Contains anti-corrosive and inorganic pigments



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

3388 FBS METAL PRIMER

BESKRIVELSE

Epoxy/Polyamide binder with anti-corrosive and inorganic pigments and thinned with alcohol solvents.

ANBEFALET BRUG

A low odour, high performance two pack epoxy primer for manually cleaned steel. Particular of interest in 'safety' areas where 'blast cleaning' is not allowed.

TEKNISK DATA

Tæthed:	1.77
Glansgrad:	Mat
Tørstofindhold i volumen:	Appr.. 68%
Blandingsforhold:	2.75:1.25 by volume Base:Activator

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	8-16 hours
Håndteringstør:	24 hours
Genbehandlingstør:	min. 24 hours - max 24 days
Brugstid:	45 minutes at 20°C

ANBEFALET VÅDFILMTYKKELSE

145 micron

ANBEFALET TØRFILMTYKKELSE

100 micron

TEORETISK FORBRUG

7 m2 per litre

PRAKTISK FORBRUG

5-6 m2 per litre

FORBEHANDLING AF OVERFLADEN

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. For optimum results remove rust, rust scale, mill scale and deteriorated coatings by abrasive blasting to Sa 2½ (ISO 8501-1 : 1988), blast profile max. 50 µm. Sand previous coatings which are in good condition to roughen the surface slightly. The surface must be clean and dry during application.

BRUGSANVISNING

Brushing or spraying for structural steel work. Airless spray is preferred for large areas such as storage tanks.

ANVENDELSESBETINGELSER

Below 8°C cure times will be significantly extended. At very low temperatures, cure may be curtailed. Product will only tolerate a dampness of surface - not running water.

PÅFØRING OG FORTYNDING: PENSEL

Do not thin

RENGØRING AF UDSKYR/SPILD

Thinner 150

SIKKERHEDSDATA

VOC-niveau:	320 g/l
VOC-kategori:	cat. A/j
VOC-grænse:	500 g/l

HOLDBARHED

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 10°C and 35°C.

Udstedelsesdato: 22/11/2023

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu