



## FK111 CLEANER/DEGREASER

### Alkaline cleaner in gel form for walls



- High-viscosity formulation is ideal for use on walls, does not run off the wall
- Removes grease, oil, proteins, dirt and many other contaminants
- Ready-use mixture, can be diluted for light pollution
- Neutralizes acids and acidic salts
- Non-flammable, virtually odour-free

KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# FK111 CLEANER/DEGREASER

## ОПИСАНИЕ

Concentrated, alkaline, non-flammable, virtually odour free, gel-like cleaning and degreasing solution for vertical substrates like walls.

## ПРЕПОРЪЧАНА УПОТРЕБА

Used to remove oil, grease, proteins and many other surface contaminations; it neutralizes acids and acidic salts. FK 111 Cleaning Solution should be applied with a stiff nylon brush or broom.

## РАЗХОДНА НОРМА

6 - 8 m<sup>2</sup>/l

## КОНСУМАЦИЯ

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

## НАЧИН НА УПОТРЕБА

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible. Scrub FK111 into the surface using a stiff (nylon) bristle brush. Allow to stand for 5 to 10 minutes and clean thoroughly by flushing with plenty of fresh water. FK111 should normally be applied as delivered. However, it can be diluted with fresh water up to 1 : 2 parts, when applied on surfaces which are slightly contaminated. Can also be used as an additive for (high-pressure) steam cleaning, in concentrations from 5% up to 25% for severely contaminated surfaces, followed by (steam) cleaning or rinsing with fresh water. After cleaning, remove any remaining water and allow to dry completely, as moisture left on the surface or entrapped into pores may cause failure of the coating system. Do not allow to dry before rinsing! Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Temperature of air, substrate and material between 5 and 35°C.

## ДАННИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС: 0 g/l  
Забележки относно безопасността: Consult Safety Data Sheet and Safety Information printed on the can.

## PH

11

## СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоително в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение бесплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

Tor Coatings Ltd (Rust-Oleum Industrial)  
Shandon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

Rust-Oleum France S.A.S.  
36, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

N.V. Martin Mathys S.A.  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)