

**RUST-OLEUM®**  
INDUSTRIAL



**3202 GALVINOLEUM®**

## Super adhesion primer

- Adheres to all smooth metal, like galvanized and stainless steel, aluminium, plastics etc.
- Recoatable after just 30 minutes
- Very high coverage: 50 m<sup>2</sup>/l
- Also for use on glass, plastics and porcelain
- Single pack product

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# 3202 GALVINOLEUM®

## DESCRIPTION

Single pack super adhesion primer for galvanised steel, plastic or other smooth surfaces.

## DOPORUČENÉ POUŽITÍ

Galvinoleum 3202 should be used on galvanised steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces. Only intended for brush application. Can be recoated with Alkythane® 7500, improving the adhesion on very smooth and non-porous surfaces.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	0,92
Úroveň lesku:	Gloss
Třída koroze:	Nizká ochrana C1/C2
Obsah pevných látek v hmotnosti:	20%
Obsah pevných látek v objemu:	16%
Tepelná odolnost:	100 °C (dry heat)

## DRY TIMES BY 20° C/RH 50%

Dotykem suché:	Remains tacky
Suché na manipulaci:	Remains tacky
Suchý nátěr:	After 30 minutes but within 24 hours
Plně vytvrzené:	24 hours

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

25-30 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

4-5 µm

## TEORETICKÁ SPOTŘEBA

35 m<sup>2</sup>/l

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove previous coatings completely. Remove salts, 'white rust', etc., by washing with Surfa-Etch 108 Etching Solution. The surface must be clean and dry during application.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Use natural bristles, long hair brushes.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Not recommended.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Use RUST-OLEUM Thinner 160 or aromatic hydrocarbons.

## POZNÁMKY

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

## SAFETY DATA

Úroveň těkavých organických látek:	745 g/l
VOC ready mix:	745 g/l
Kategorie VOC:	A/h
Limitní hodnota VOC:	750 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 20/03/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu