

RUST-OLEUM®
INDUSTRIAL



3202 GALVINOLEUM®

Super adhesion primer

- Adheres to all smooth metal, like galvanized and stainless steel, aluminium, plastics etc.
- Recoatable after just 30 minutes
- Very high coverage: 50 m²/l
- Also for use on glass, plastics and porcelain
- Single pack product

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

3202 GALVINOLEUM®

BESKRIVELSE

Single pack super adhesion primer for galvanised steel, plastic or other smooth surfaces.

ANBEFALT BRUK

Galvinoleum 3202 should be used on galvanised steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces. Only intended for brush application. Can be recoated with Alkythane® 7500, improving the adhesion on very smooth and non-porous surfaces.

TEKNISKE DATA

Tetthet:	0,92
Glansgrad:	Blank
Korrosjonsklasse:	C1/C2 lav beskyttelse
Tørrstoffinnhold i vekt:	20%
Tørrstoffinnhold i volum:	16%
Varmebestandig:	100 °C (dry heat)

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	Remains tacky
Håndtørbar:	Remains tacky
Overmalbar:	After 30 minutes but within 24 hours
Herdetid:	24 hours

ANBEFALT VÅTFILMYKKELSE

25-30 µm

ANBEFALT TØRRFILMYKKELSE

4-5 µm

TEORETISK FORBRUK

35 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove previous coatings completely. Remove salts, 'white rust', etc., by washing with Surfa-Etch 108 Etching Solution. The surface must be clean and dry during application.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

PÅFØRING & FORTYNNING: PENSEL

Use natural bristles, long hair brushes.

PÅFØRING & FORTYNNING: RULLE

Not recommended.

RENGJØRING AV UTSTYR/SPILL

Use RUST-OLEUM Thinner 160 or aromatic hydrocarbons.

MERKNADER

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

SIKKERHETSDATA

VOC nivå:	745 g/l
VOC ferdigblandet:	745 g/l
VOC kategori:	A/h
VOC grense:	750 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 20/03/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu