

RUST-OLEUM®
INDUSTRIAL



3202 GALVINOLEUM®

Super adhesion primer

- Adheres to all smooth metal, like galvanized and stainless steel, aluminium, plastics etc.
- Recoatable after just 30 minutes
- Very high coverage: 50 m²/l
- Also for use on glass, plastics and porcelain
- Single pack product

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

3202 GALVINOLEUM®

DESCRIPTION

Single pack super adhesion primer for galvanised steel, plastic or other smooth surfaces.

ODPORÚČANÉ POUŽITIE

Galvinoleum 3202 should be used on galvanised steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces. Only intended for brush application. Can be recoated with Alkythane® 7500, improving the adhesion on very smooth and non-porous surfaces.

TECHNICAL DATA

Hustota (g/cm ³):	0,92
Úroveň lesku:	Gloss
Trieda korózie:	C1/C2 nízka ochrana
Obsah pevných látok v hmotnosti:	20%
Obsah pevných látok v objeme:	16%
Tepelná odolnosť:	100 °C (dry heat)

DRY TIMES BY 20° C/RH 50%

Na dotyk suché:	Remains tacky
Suché na manipuláciu:	Remains tacky
Suchý na opätovné natieranie:	After 30 minutes but within 24 hours
Úplne vytvrdené:	24 hours

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

25-30 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

4-5 µm

TEORETICKÁ SPOTREBA

35 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Remove previous coatings completely. Remove salts, 'white rust', etc., by washing with Surfa-Etch 108 Etching Solution. The surface must be clean and dry during application.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%. The substrate temperature must be at least 3°C above dew point.

APLIKÁCIA A RIEDENIE: ŠTETEC

Use natural bristles, long hair brushes.

APLIKÁCIA A RIEDENIE: VALEC

Not recommended.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Use RUST-OLEUM Thinner 160 or aromatic hydrocarbons.

POZNÁMKY

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

SAFETY DATA

Úroveň VOC:	745 g/l
VOC readymix:	745 g/l
Kategória VOC:	A/h
Limit VOC:	750 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 13/05/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu