

RUST-OLEUM®
INDUSTRIAL



GRAFFITISHIELD™ HYDRO

Water-based anti-graffiti coating

- Ideal for natural stone types
- Almost invisible result
- No film building
- Excellent UV-resistance
- Transparent protection

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

GRAFFITISHIELD™ HYDRO

DESCRIPTION

Water based permanent anti-graffiti coating with hydrophobic properties for mineral substrates.

DOPORUČENÉ POUŽITÍ

GraffitiShield™ HYDRO can be applied to all porous mineral surfaces, such as concrete, brickwork, and dimension stone.

TECHNICAL DATA

Hustota (g/cm³): 1,0
Úroveň lesku: Matt
Obsah pevných látek v objemu: 10%

DRY TIMES BY 20° C/RH 50%

Dotykem suché: 1 hour
Suché na manipulaci: 1 hour
Suchý nátěr: 1 hour (with itself)
Plně vytvrzené: 3 days

TEORETICKÁ SPOTŘEBA

5 - 10 m²/l

PRAKTICKÁ SPOTŘEBA

Dependent on many factors, such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

The surface should be clean, dry, and free of dirt and grease.

NÁVOD K POUŽITÍ

Before use, shake up and stir well to ensure a good degree of homogeneity. Lay on two coats, with a drying interval of at least 60 minutes between coats.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Do not dilute. Nozzle 013-015. It is advisable to cover up windows and doors during application.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Do not dilute. It is advisable to cover up windows and doors during application.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

POZNÁMKY

Remove graffiti with GraffitiShield™ CLEANER. GraffitiShield™ HYDRO will remain fully intact once graffiti has been removed, allowing for many rounds of cleaning.

SAFETY DATA

Úroveň těkavých organických látek: 51 g/l
VOC readymix: 51 g/l
Kategorie VOC: A/i
Limitní hodnota VOC: 140 g/l
Poznámky k bezpečnosti: Consult the relevant product safety sheet and information on the packaging.

DOBA POUŽITELNOSTI

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.

last_updated: 13/05/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu