

**RUST-OLEUM®**  
INDUSTRIAL



## GRAFFITISHIELD™ HYDRO

# Water-based anti-graffiti coating

- Ideal for natural stone types
- Almost invisible result
- No film building
- Excellent UV-resistance
- Transparent protection

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# GRAFFITISHIELD™ HYDRO

## BESKRIVELSE

Water based permanent anti-graffiti coating with hydrophobic properties for mineral substrates.

## ANBEFALT BRUK

GraffitiShield™ HYDRO can be applied to all porous mineral surfaces, such as concrete, brickwork, and dimension stone.

## TEKNISKE DATA

Tetthet: 1,0  
Glansgrad: Matt  
Tørrstoffinnhold i volum: 10%

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr: 1 hour  
Håndterbar: 1 hour  
Overmalbar: 1 hour (with itself)  
Herdetid: 3 days

## TEORETISK FORBRUK

5 - 10 m<sup>2</sup>/l

## PRAKTISK FORBRUK

Dependent on many factors, such as porosity and roughness of the substrate and material losses during application.

## KLARGJØRING AV OVERFLATE

The surface should be clean, dry, and free of dirt and grease.

## BRUKSANVISNING

Before use, shake up and stir well to ensure a good degree of homogeneity. Lay on two coats, with a drying interval of at least 60 minutes between coats.

## PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Do not dilute. Nozzle 013-015. It is advisable to cover up windows and doors during application.

## PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Do not dilute. It is advisable to cover up windows and doors during application.

## RENGJØRING AV UTSTYR/SPILL

Water.

## MERKNADER

Remove graffiti with GraffitiShield™ CLEANER. GraffitiShield™ HYDRO will remain fully intact once graffiti has been removed, allowing for many rounds of cleaning.

## SIKKERHETSDATA

VOC nivå: 51 g/l  
VOC ferdigblandet: 51 g/l  
VOC kategori: A/i  
VOC grense: 140 g/l  
Merknader angående sikkerhet: Consult the relevant product safety sheet and information on the packaging.

## HOLDBARHET

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.

Utstedt dato: 20/03/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

### Rust-Oleum Netherlands B.V.

Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

### Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

### Rust-Oleum France S.A.S.

38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

### N.V. Martin Mathys S.A.

Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu