

**RUST-OLEUM®**  
INDUSTRIAL



## GRAFFITISHIELD™ HYDRO

# Water-based anti-graffiti coating

- Ideal for natural stone types
- Almost invisible result
- No film building
- Excellent UV-resistance
- Transparent protection

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# GRAFFITISHIELD™ HYDRO

## BESKRIVNING

Water based permanent anti-graffiti coating with hydrophobic properties for mineral substrates.

## REKOMMENDERAD ANVÄNDNING

GraffitiShield™ HYDRO can be applied to all porous mineral surfaces, such as concrete, brickwork, and dimension stone.

## TEKNISK DATA

Densitet: 1,0  
Glansnivå: Matt  
Torrsubstansvolym: 10%

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr: 1 hour  
Hanteringstorr: 1 hour  
Torktid: 1 hour (with itself)  
Fullt härdad: 3 days

## ÅTGÅNG

5 - 10 m<sup>2</sup>/l

## ÅTGÅNG INFORMATION

Dependent on many factors, such as porosity and roughness of the substrate and material losses during application.

## FÖRBEREDELSE

The surface should be clean, dry, and free of dirt and grease.

## APPLICERING

Before use, shake up and stir well to ensure a good degree of homogeneity. Lay on two coats, with a drying interval of at least 60 minutes between coats.

## APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Do not dilute. Nozzle 013-015. It is advisable to cover up windows and doors during application.

## APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Do not dilute. It is advisable to cover up windows and doors during application.

## RENGÖRING AV REDSKAP/SPILL

Water.

## INFORMATION

Remove graffiti with GraffitiShield™ CLEANER. GraffitiShield™ HYDRO will remain fully intact once graffiti has been removed, allowing for many rounds of cleaning.

## SÄKERHETSDATA

VOC-nivå: 51 g/l  
VOC färdigmix: 51 g/l  
VOC-kategori: A/i  
VOC-gräns: 140 g/l  
Anmärkningar om säkerhet: Consult the relevant product safety sheet and information on the packaging.

## HÅLLBARHET

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.

Utgivningsdatum: 13/05/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)