

RUST-OLEUM®
INDUSTRIAL



GRAFFITISHIELD™ WAX

Anti-graffiti coating based on bee wax



- Virtually invisible sacrificial coating for many surface types
- Biodegradable
- Resistant against UV and weathering
- Low solvent content
- Water vapour permeable

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

GRAFFITISHIELD™ WAX

ОПИСАНИЕ

Sacrificial layer based on natural wax. Suitable for a single cleaning process.

ПРЕПОРЪЧНА УПОТРЕБА

Once it has hardened, GraffitiShield™ WAX is very resistant to many types of ink and paint. Graffiti can be easily removed with hot water. Once the graffiti has been removed, the cleaned areas should once again be coated with GraffitiShield™ WAX. Once the hardening period has passed, this will ensure that the treated surface is once again resistant to graffiti. Suitable surfaces: dimension stone, brick, calcium silicate, concrete, acrylic, and marble. It is important that the surfaces used can be cleaned under high pressures, at a water temperature of 70-90°C.

ТЕХНИЧЕСКИ ДАННИ

Пълтност (г/см³): 1,02
Гланцово ниво: satin

ВРЕМЕ ЗА СУШЕНЕ ДО 20° С/RH 50%

Сух на допир: 1 hour
Сух за употреба: 12 hours
Готов за повторно нанасяне: 2 hours
Напълно втвърден: 24 hours

РАЗХОДНА НОРМА

6,7 м²/l

КОНСУМАЦИЯ

Dependent on many factors, such as porosity and roughness of the surface and material losses during application (see DIN 53220).

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The surface should be clean, dry, and free of dirt and grease.

НАЧИН НА УПОТРЕБА

Before use, shake up and stir well to ensure a good degree of homogeneity.

УСЛОВИЯ ЗА НАНАСЯНЕ

The working temperature range is between 5°C and 35°C.

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Warm water.

ЗАБЕЛЕЖКИ

Graffiti can be easily removed with a high-pressure cleaner and hot water. When spraying at pressures of 40 bar and upwards, and a minimum temperature of 70-90°C, GraffitiShield™ Wax will melt, removing the graffiti from the surface along with it. After removal, a new layer of GraffitiShield™ Wax should be applied.

ДАННИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	25 g/l
Готов за употреба ЛОС (VOC Readymix):	25 g/l
Категория ЛОС:	A/c
Ограничение за ЛОС:	40 g/l
Забележки относно безопасността:	Consult the relevant product safety sheet and information on the packaging.

СРОК НА ГОДНОСТ

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.

Дата на издаване: 20/03/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоително в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение бесплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shandon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
36, av. du Gros Chêne
95522 Herblay
France
T: +33(0) 13 40 00 44
F: +33(0) 13 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu