

**RUST-OLEUM®**  
INDUSTRIAL



## GRAFFITISHIELD™ WAX

# Anti-graffiti coating based on bee wax

- Virtually invisible sacrificial coating for many surface types
- Biodegradable
- Resistant against UV and weathering
- Low solvent content
- Water vapour permeable

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# GRAFFITISHIELD™ WAX

## DESCRIPTION

Sacrificial layer based on natural wax. Suitable for a single cleaning process.

## RECOMMENDED USE

Once it has hardened, GraffitiShield™ WAX is very resistant to many types of ink and paint. Graffiti can be easily removed with hot water. Once the graffiti has been removed, the cleaned areas should once again be coated with GraffitiShield™ WAX. Once the hardening period has passed, this will ensure that the treated surface is once again resistant to graffiti. Suitable surfaces: dimension stone, brick, calcium silicate, concrete, acrylic, and marble. It is important that the surfaces used can be cleaned under high pressures, at a water temperature of 70-90°C.

## TECHNICAL DATA

Density (g/cm³): 1,02  
Gloss Level: Satin

## DRY TIMES BY 20° C/RH 50%

Touch dry: 1 hour  
Dry to handle: 12 hours  
Dry to recoat: 2 hours  
Fully cured: 24 hours

## THEORETICAL CONSUMPTION

6,7 m²/l

## PRACTICAL CONSUMPTION

Dependent on many factors, such as porosity and roughness of the surface and material losses during application (see DIN 53220).

## SURFACE PREPARATION

The surface should be clean, dry, and free of dirt and grease.

## DIRECTIONS FOR USE

Before use, shake up and stir well to ensure a good degree of homogeneity.

## APPLICATION CONDITIONS

The working temperature range is between 5°C and 35°C.

## APPLICATION & THINNING: AIRLESS SPRAY

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

## CLEANING OF EQUIPMENT / SPILLS

Warm water.

## REMARKS

Graffiti can be easily removed with a high-pressure cleaner and hot water. When spraying at pressures of 40 bar and upwards, and a minimum temperature of 70-90°C, GraffitiShield™ Wax will melt, removing the graffiti from the surface along with it. After removal, a new layer of GraffitiShield™ Wax should be applied.

## SAFETY DATA

VOC level: 25 g/l  
VOC ready mix: 25 g/l  
VOC category: A/c  
VOC limit: 40 g/l  
Remarks regarding safety: Consult the relevant product safety sheet and information on the packaging.

## SHELF LIFE

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.

Date issued: 20/03/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu