

RUST-OLEUM®
INDUSTRIAL



GRAFFITISHIELD™ WAX

Anti-graffiti coating based on bee wax



- Virtually invisible sacrificial coating for many surface types
- Biodegradable
- Resistant against UV and weathering
- Low solvent content
- Water vapour permeable

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

GRAFFITISHIELD™ WAX

BESKRIVELSE

Sacrificial layer based on natural wax. Suitable for a single cleaning process.

ANBEFALT BRUK

Once it has hardened, GraffitiShield™ WAX is very resistant to many types of ink and paint. Graffiti can be easily removed with hot water. Once the graffiti has been removed, the cleaned areas should once again be coated with GraffitiShield™ WAX. Once the hardening period has passed, this will ensure that the treated surface is once again resistant to graffiti. Suitable surfaces: dimension stone, brick, calcium silicate, concrete, acrylic, and marble. It is important that the surfaces used can be cleaned under high pressures, at a water temperature of 70-90°C.

TEKNISKE DATA

Tetthet:	1,02
Glansgrad:	Satinert

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	1 hour
Håndterbar:	12 hours
Overmalbar:	2 hours
Herdetid:	24 hours

TEORETISK FORBRUK

6,7 m²/l

PRAKTIK FORBRUK

Dependent on many factors, such as porosity and roughness of the surface and material losses during application (see DIN 53220).

KLARGJØRING AV OVERFLATE

The surface should be clean, dry, and free of dirt and grease.

BRUKSANVISNING

Before use, shake up and stir well to ensure a good degree of homogeneity.

PAFØRINGSBETINGELSER

The working temperature range is between 5°C and 35°C.

PAFØRING & FORTYNNING: LUFTFRI SPRØYTE

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

PAFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

RENGJØRING AV UTSTYR/SPILL

Warm water.

MERKNADER

Graffiti can be easily removed with a high-pressure cleaner and hot water. When spraying at pressures of 40 bar and upwards, and a minimum temperature of 70-90°C, GraffitiShield™ Wax will melt, removing the graffiti from the surface along with it. After removal, a new layer of GraffitiShield™ Wax should be applied.

Utstedt dato: 20/03/2025

SIKKERHETSDATA

VOC nivå:	25 g/l
VOC ferdigblandet:	25 g/l
VOC kategori:	A/c
VOC grense:	40 g/l
Merknader angående sikkerhet:	Consult the relevant product safety sheet and information on the packaging.

HOLDBARHET

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.