

**RUST-OLEUM®**  
INDUSTRIAL



## GRAFFITISHIELD™ WAX

# Anti-graffiti coating based on bee wax

- Virtually invisible sacrificial coating for many surface types
- Biodegradable
- Resistant against UV and weathering
- Low solvent content
- Water vapour permeable

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# GRAFFITISHIELD™ WAX

## BESKRIVELSE

Sacrificial layer based on natural wax. Suitable for a single cleaning process.

## ANBEFALT BRUK

Once it has hardened, GraffitiShield™ WAX is very resistant to many types of ink and paint. Graffiti can be easily removed with hot water. Once the graffiti has been removed, the cleaned areas should once again be coated with GraffitiShield™ WAX. Once the hardening period has passed, this will ensure that the treated surface is once again resistant to graffiti. Suitable surfaces: dimension stone, brick, calcium silicate, concrete, acrylic, and marble. It is important that the surfaces used can be cleaned under high pressures, at a water temperature of 70-90°C.

## TEKNISKE DATA

Tetthet: 1,02  
Glansgrad: Satinert

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr: 1 hour  
Håndterbar: 12 hours  
Overmalbar: 2 hours  
Herdetid: 24 hours

## TEORETISK FORBRUK

6,7 m<sup>2</sup>/l

## PRAKTISK FORBRUK

Dependent on many factors, such as porosity and roughness of the surface and material losses during application (see DIN 53220).

## KLARGJØRING AV OVERFLATE

The surface should be clean, dry, and free of dirt and grease.

## BRUKSANVISNING

Before use, shake up and stir well to ensure a good degree of homogeneity.

## PÅFØRINGSBETINGELSER

The working temperature range is between 5°C and 35°C.

## PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

## PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Do not dilute. Lay on crosswise in two coats, wet-on-wet, with a break of 10 minutes to 2 hours between the coats. It is advisable to cover up windows and doors during application.

## RENGJØRING AV UTSTYR/SPILL

Warm water.

## MERKNADER

Graffiti can be easily removed with a high-pressure cleaner and hot water. When spraying at pressures of 40 bar and upwards, and a minimum temperature of 70-90°C, GraffitiShield™ Wax will melt, removing the graffiti from the surface along with it. After removal, a new layer of GraffitiShield™ Wax should be applied.

## SIKKERHETSDATA

VOC nivå: 25 g/l  
VOC ferdigblandet: 25 g/l  
VOC kategori: A/c  
VOC grense: 40 g/l  
Merknader angående sikkerhet: Consult the relevant product safety sheet and information on the packaging.

## HOLDBARHET

Minimum of 1 year from production date, provided it is stored in the unopened original packaging, in a dry, well-ventilated space, away from direct sunlight, at a temperature between 0° and 30°C.

Utstedt dato: 13/05/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

### Rust-Oleum Netherlands B.V.

Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

### Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

### Rust-Oleum France S.A.S.

38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

### N.V. Martin Mathys S.A.

Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu