

RUST-OLEUM®
INDUSTRIAL



HARD HAT® ADHESION PRIMER

Undercoat for difficult substrates

- Ready to recoat after just 30 minutes
- Unique coverage: 5.5 m² per aerosol
- To recoat with HARD HAT® topcoats
- Wide angle spray pattern for a large and even coverage

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

HARD HAT® ADHESION PRIMER

BESKRIVELSE

RUST-OLEUM® Hard Hat Aerosol 2102 Adhesion Primer is an adhesion coat based on a solvent containing acrylic.

ANBEFALT BRUK

RUST-OLEUM 2102 Adhesion Primer should be used on galvanized steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces followed by RUST-OLEUM Hard Hat 2100 Topcoats. RUST-OLEUM 2102 Adhesion Primer is intended for small maintenance jobs. RUST-OLEUM 2102 Adhesion Primer should be used in light industrial exposures, normal humidity and interior applications.

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	Remains tacky
Håndterbar:	Remains tacky
Overmalbar:	After 30 minutes but within 24 hours

TEORETISK FORBRUK

5.5 m² per spray can

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Remove dirt, grease, oil and all other surface contaminants by appropriate means. Remove previous coatings completely e.g. with RUST-OLEUM Paint Stripper 2925. The surface must be clean and dry during application.

PÅFØRINGSBETINGELSER

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

PÅFØRING & FORTYNNING: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can at least 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply a single, thin layer and avoid application of thick layers. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

MERKNADER

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

SIKKERHETSDATA

VOC nivå:	730 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 13/05/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu