

RUST-OLEUM®
INDUSTRIAL



HARD HAT® ADHESION PRIMER

Undercoat for difficult substrates

- Ready to recoat after just 30 minutes
- Unique coverage: 5.5 m² per aerosol
- To recoat with HARD HAT® topcoats
- Wide angle spray pattern for a large and even coverage

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

HARD HAT® ADHESION PRIMER

BESKRIVNING

RUST-OLEUM® Hard Hat Aerosol 2102 Adhesion Primer is an adhesion coat based on a solvent containing acrylic.

REKOMMENDERAD ANVÄNDNING

RUST-OLEUM 2102 Adhesion Primer should be used on galvanized steel, stainless steel, aluminium, copper, glass, porcelain and other smooth, dense surfaces followed by RUST-OLEUM Hard Hat 2100 Topcoats. RUST-OLEUM 2102 Adhesion Primer is intended for small maintenance jobs. RUST-OLEUM 2102 Adhesion Primer should be used in light industrial exposures, normal humidity and interior applications.

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

| | |
|-----------------|--------------------------------------|
| Beröringstorr: | Remains tacky |
| Hanteringstorr: | Remains tacky |
| Torktid: | After 30 minutes but within 24 hours |

ÅTGÅNG

5.5 m² per spray can

ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FÖRBEREDELSE

Remove dirt, grease, oil and all other surface contaminants by appropriate means. Remove previous coatings completely e.g. with RUST-OLEUM Paint Stripper 2925. The surface must be clean and dry during application.

APPLICERINGSFÖRHÅLLANDEN

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

APPLICERING OCH SPÄDNING: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can at least 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply a single, thin layer and avoid application of thick layers. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

INFORMATION

Recoat as soon as possible after 30 minutes to avoid dust/dirt entrapment in the tacky coat.

SÄKERHETSDATA

| | |
|---------------------------|--|
| VOC-nivå: | 730 g/l |
| Anmärkningar om säkerhet: | Consult Safety Data Sheet and Safety Information printed on the can. |

HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 13/05/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu