

# RUST-OLEUM®

INDUSTRIAL



## HARD HAT® TOPCOAT FLUORESCENT

# Fluorescent topcoat



- Highly visible fluorescent coatings
- Ideal for railings, signs, colour coding etc.
- First apply matt white 2190 for best results
- Finish with transparent topcoat for better gloss
- To handle after 30 minutes (at 20°C)

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# HARD HAT® TOPCOAT FLUORESCENT

## DESCRIPTION

Hard Hat® Aerosol Topcoats 2200 are based on a fast drying short oil soya alkyd. The products are based on lead- and chromate free pigments.

## DOPORUČENÉ POUŽITÍ

RUST-OLEUM Fluorescent Topcoats 2200 should be applied over RUST-OLEUM Hard Hat 2190 Flat White; for exterior applications it is recommended to recoat Fluorescent Topcoats 2200 with RUST-OLEUM Hard Hat 2500 Clear. RUST-OLEUM Fluorescent Topcoats 2200 are intended for safety marking or signalling. RUST-OLEUM Fluorescent Topcoats 2200 should be used in light industrial exposures, normal humidity and interior applications.

## TECHNICAL DATA

Úroveň lesku: Matt  
Tepelná odolnost: 100°C (dry heat)

## DRY TIMES BY 20° C/RH 50%

Dotykem suché: 15 minutes  
Suché na manipulaci: 30 minutes  
Suchý nátěr: After 1 hour  
Plně vytvrzené: 3 days

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

25 µm

## TEORETICKÁ SPOTŘEBA

2.1 m<sup>2</sup> per spray can at 25 µm dry

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

Remove dirt, grease, oil and all other surface contaminants by appropriate means. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

## PODMÍNKY POUŽITÍ

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

## APLIKACE A ŘEDĚNÍ: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

## POZNÁMKY

Fluorescent topcoats should be applied on a white substrate for maximum brightness. At UV-light exposure the colour tends to fade, the speed of fading is directly proportional to the dry film thickness and the intensity of the UV-light.

## SAFETY DATA

Úroveň těkavých organických látek: 653 g/l  
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 13/05/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu