

RUST-OLEUM®

INDUSTRIAL



HARD HAT® TOPCOAT FLUORESCENT

Fluorescent topcoat



- Highly visible fluorescent coatings
- Ideal for railings, signs, colour coding etc.
- First apply matt white 2190 for best results
- Finish with transparent topcoat for better gloss
- To handle after 30 minutes (at 20°C)

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

HARD HAT® TOPCOAT FLUORESCENT

DESCRIPTION

Hard Hat® Aerosol Topcoats 2200 are based on a fast drying short oil soya alkyd. The products are based on lead- and chromate free pigments.

ODPORÚČANÉ POUŽITIE

RUST-OLEUM Fluorescent Topcoats 2200 should be applied over RUST-OLEUM Hard Hat 2190 Flat White; for exterior applications it is recommended to recoat Fluorescent Topcoats 2200 with RUST-OLEUM Hard Hat 2500 Clear. RUST-OLEUM Fluorescent Topcoats 2200 are intended for safety marking or signalling. RUST-OLEUM Fluorescent Topcoats 2200 should be used in light industrial exposures, normal humidity and interior applications.

TECHNICAL DATA

Úroveň lesku: Matt
Tepelná odolnosť: 100°C (dry heat)

DRY TIMES BY 20° C/RH 50%

Na dotyk suché: 15 minutes
Suché na manipuláciu: 30 minutes
Suchý na opätovné natieranie: After 1 hour
Úplne vytvrdnuté: 3 days

ODPORÚČANÁ HRÚBK A MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRÚBK A SUCHÉHO FILMU

25 µm

TEORETICKÁ SPOTREBA

2.1 m² per spray can at 25 µm dry

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Remove dirt, grease, oil and all other surface contaminants by appropriate means. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

PODMIENKY APLIKÁCIE

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

APLIKÁCIA A RIEDENIE: AEROSÓL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

POZNÁMKY

Fluorescent topcoats should be applied on a white substrate for maximum brightness. At UV-light exposure the colour tends to fade, the speed of fading is directly proportional to the dry film thickness and the intensity of the UV-light.

SAFETY DATA

Úroveň VOC: 653 g/l
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 13/05/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu