


**RUST-OLEUM®**  
— INDUSTRIAL —



## HARD HAT® GALVA EXPRESSE

# Quick-drying protection

- Protection and quick drying in one
- Tack free after just 5 minutes, to handle after 10 minutes
- Ideal for production and construction environments
- Resists 400 hours of salt spray testing (DIN 50021 SS)

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# HARD HAT® GALVA EXPRESSE

## DESCRIZIONE

Hard Hat® Aerosol Galva Expresse 2180 is a very fast drying zinc rich primer based on a styrene-acrylic resin. The product contains pure zinc as pigment and provides excellent protection against corrosion.

## UTILIZZO CONSIGLIATO

RUST-OLEUM Galva Expresse 2180 should be used on new, bare steel or galvanised steel surfaces. RUST-OLEUM Galva Expresse 2180 is intended to be applied on small areas or for touch-up. RUST-OLEUM Galva Expresse 2180 can be recoated with non-saponifiable coatings. RUST-OLEUM Galva Expresse 2180 should be used as a primer or as a single coat in light industrial exposures, corrosive environments and high humidity areas.

## DATI TECNICI

Livello di lucentezza: Opaco  
Resistenza al calore: 350°C (dry heat)

## TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto al tatto: 5 minutes  
Asciutto da maneggiare: 10 minutes  
Asciutto da rivestire: Within 1 hour or after 48 hours  
Completamente indurito: 3 days

## SPESSORE DELLA PELLICOLA UMIDA CONSIGLIATO

100 µm

## SPESSORE DELLA PELLICOLA ASCIUTTA CONSIGLIATO

35 µm

## CONSUMO TEORICO

1.4 m<sup>2</sup> per spray can at 35 µm dry

## CONSUMO PRATICO

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PREPARAZIONE DELLA SUPERFICIE

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. The surface must be clean and dry during application.

## CONDIZIONI DI APPLICAZIONE

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

## APPLICAZIONE E DILUIZIONE: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply a full, wet coat to achieve a close, dense coating film, avoid dry spray. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

## NOTE

Both products are lead- and chromate free thus eliminating the danger of poisonous gases escaping if the coated surface needs to be welded at a later date.

## DATI RELATIVI ALLA SICUREZZA

Livello di COV: 645 g/l  
Note riguardanti la sicurezza: Consult Safety Data Sheet and Safety Information printed on the can.

## SCADENZA

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data del rilascio: 13/05/2025

**Colori e formati di confezione disponibili:** Si prega di consultare la pagina relativa al prodotto su [www.rust-oleum.eu](http://www.rust-oleum.eu) per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

**Dichiarazione di non responsabilità:** Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da [www.rust-oleum.eu](http://www.rust-oleum.eu) o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu