

RUST-OLEUM®
INDUSTRIAL



HARD HAT® GALVA ZINC

Cathodic protection of bare and galvanised steel

- Cathodic protection of bare and galvanised steel
- 90% pure zinc in dry paint film
- Resists 500 hours of salt spray testing (DIN 50021 SS)
- To recoat within one hour, brush version after 4 hours
- To recoat with HARD HAT® metallic sprays

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

HARD HAT® GALVA ZINC

ОПИСАНИЕ

Hard Hat® Aerosol Zinc Spray Cold Galvanising Compound 2185 is a fast drying zinc rich primer based on an epoxy ester resin. The product contains pure zinc as pigment and provides cathodic protection.

ПРЕПОРЪЧАНА УПОТРЕБА

RUST-OLEUM Zinc Spray 2185 should be used on new, bare steel or galvanised steel surfaces. RUST-OLEUM Zinc Spray 2185 is intended to be applied on small areas or for touch-up. RUST-OLEUM Zinc Spray 2185 can be recoated with non-saponifiable coatings. RUST-OLEUM Zinc Spray 2185 should be used as a primer or as a single coat in light industrial exposures, corrosive environments and high humidity areas.

ТЕХНИЧЕСКИ ДАННИ

Гланцово ниво: Мат
Топлинна устойчивост: 450°C (dry heat)

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир: 10 minutes
Сух за употреба: 30 minutes
Готов за повторно нанасяне: Within 1 hour or after 48 hours
Напълно втвърден: 7 days

МОКЪР СЛОЙ

100 µm

СУХ СЛОЙ

35 µm

РАЗХОДНА НОРМА

1,4 m² per spray can at 35 µm dry

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. The surface must be clean and dry during application.

УСЛОВИЯ ЗА НАНАСЯНЕ

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

GROUP APPL THINNING 60 AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply a full, wet coat to achieve a close, dense coating film, avoid dry spray. After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС: 630 g/l
Забележки относно безопасността: Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 13/05/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu