



HARD HAT® TOPCOAT HEAT RESISTANT

Heat resistant coating up to 750°C



- For continuous temperatures up to 650°C
- For peak temperatures up to 750°C
- For on bare metal or slightly rusted surfaces
- Ideal for engines, heat cannons, pipes, vents, etc.
- To handle after 3 hours (at 20°C)

HARD HAT® TOPCOAT HEAT RESISTANT

ОПИСАНИЕ

Hard Hat® 1015 and 1078 are Heat Resistant Coatings based on a silicone modified alkyd resin.

ПРЕПОРЪЧАНА УПОТРЕБА

HARD HAT® Heat Resistant Coating can be applied on new, bright or shot-blasted steel or well pre-treated coated surfaces such as barbecues, boiler fittings, hot air cannons, exhausts, etc.

HARD HAT® Heat Resistant Coating is intended for small maintenance jobs and repairs. HARD HAT® Heat Resistant Coating provides protection up to a dry heat of 750°C (short term peak load) for applications indoors or in a sheltered outdoor environment.

ТЕХНИЧЕСКИ ДАННИ

Гланцово ниво:	matt
corrosion_class:	n_a
heat_resistance:	Standard 600°C (dry heat) / Short term peak 750°C (dry heat)

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	2 hours
Сух за употреба:	8 hours
Готов за повторно нанасяне:	24 hours
Напълно втвърден:	Allow the product to dry for 3 hours at room temperature and then heat to 150°C in stages of max. 50°C/hour. Allow to cool for 24 hours. The product is now fully cured.

МОКЪР СЛОЙ

85 µm

СУХ СЛОЙ

35-40 µm

РАЗХОДНА НОРМА

10-12 m² per litre at 35 - 40 µm dry

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

НАЧИН НА УПОТРЕБА

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

УСЛОВИЯ ЗА НАНАСЯНЕ

Only apply if the air and surface temperatures are between 5 and 35°C and the relative humidity is less than 85%.

The temperature of the coated surface must be at least 3°C above the dew point.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

No thinning

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

No thinning. Use shorthaired polyamide (perlon 8 - 12 mm) rollers

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Dilute up to 10 to 15% volume RUST-OLEUM Thinner 7301

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

With RUST-OLEUM thinners 7301.

ЗАБЕЛЕЖКИ

RUST-OLEUM Heat resistant coating 1015 and 1078 are self-priming and should not be applied on primers or coatings, which are not heat resistant.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	1015: 458 g/l max / 1078: 416 g/l max
Готов за употреба ЛОС (VOC Ready mix):	1015: 458 g/l max / 1078: 416 g/l max
Категория ЛОС:	A/i
Ограничение за ЛОС:	500 g/l
Забележки относно безопасността:	Consult Safety Data Sheet and Safety information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителя е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu