

**RUST-OLEUM®**  
— INDUSTRIAL —



## **HARD HAT® MARKING AEROSOLS**



## **For quick and durable marking**

- For marking difficult substrates
- Best opacity and weather-resistant
- For on metal, concrete, asphalt, gravel, soil, grass, wood, etc.
- Even on slightly wet surfaces
- Upside down spraying system

**KNOW-HOW TO PROTECT™**

**WWW.RUST-OLEUM.EU**



# HARD HAT® MARKING AEROSOLS

## DESCRIPTION

For quick and easy marking of construction and excavation sites, underground utilities and for traffic safety.

## RECOMMENDED USE

RUST-OLEUM Marking Paint 2300 should be used on metal, concrete, asphalt, gravel, soil and grass, etc. RUST-OLEUM Marking Paint 2300 is not water-soluble and should be used in light industrial exposures, normal humidity and interior applications. RUST-OLEUM Marking Paint 2300 is designed for quick and easy marking of construction and excavation sites, underground utilities and for traffic safety.

## TECHNICAL DATA

Gloss Level: Matt  
Heat Resistance: 100°C (dry heat)

## DRY TIMES BY 20° C/RH 50%

Touch dry: 20 minutes  
Dry to handle: 4 hours  
Dry to recoat: Within 1 hour or after 48 hours

## RECOMMENDED DRY FILM THICKNESS

25 µm dry

## THEORETICAL CONSUMPTION

2 m² per spray can at 25 µm dry, depending on colour.

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

## SURFACE PREPARATION

Remove dirt, grease, oil and all other surface contaminants by appropriate means. The surface must be clean and dry during application.

## APPLICATION CONDITIONS

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

## APPLICATION & THINNING: AEROSOL

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Invert can and point spray button at ground or floor. Hold can approx. 10 - 15 cm above the surface to be marked. Press spray button to start spraying. Use a steady even stroke while spraying. After use turn can upright and press spray button for 2 - 3 seconds to clean valve.

## REMARKS

Fluorescent Marking Paint should be applied on a white substrate for maximum brightness.

## SAFETY DATA

VOC level: 630 g/l  
Remarks regarding safety: Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 24/06/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)