



LEAKSEAL®

The flexible rubber coating; seals leaks and cracks

- · Watertight semi smooth finish
- Can be top-coated with latex or oil-based paints
- For use on metal, aluminum, PVC, concrete, masonry, asphalt roofing materials, etc.
- · Overcoatable with various paints

KNOW-HOW TO PROTECT™



DESCRIPTION

Designed to fill and seal leaks and cracks on metal, aluminium, galvanized metal, PVC, concrete, masonry, asphalt/bituminous roofing materials, vinyl siding, fiberglass, and more.

RECOMMENDED USE

Designed to fill and seal leaks and cracks on metal, aluminium, galvanized metal, PVC, concrete, masonry, asphalt/bituminous roofing materials, vinyl siding, fiberglass, and more

DRY TIMES BY 20° C/RH 50%

Touch dry: 20 - 30 minutes
Dry to handle: 45 - 60 minutes

Dry to recoat: Apply second layer LeakSeal after 15 - 30 minutes.

Top-coated with water-based or oil-based paints after

24 hours

Fully cured: 24 hours

RECOMMENDED DRY FILM THICKNESS

65 µm

THEORETICAL CONSUMPTION

0,74 m² per aerosol at 65 µm dry film thickness

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

SURFACE PREPARATION

Remove all dirt and debris from the area to be coated. Wash area with a detergent and water solution, rinse with fresh water, and allow the surface to dry thoroughly. Remove any loose paint or previous coatings with a wire brush or sandpaper. Lightly sand glossy surfaces. Wipe the sanded surface clean when finished. Test previous coated material for compatibility before use.

APPLICATION CONDITIONS

Use outdoors or in a well-ventilated area such as an open garage. Apply when temperature is between 50°F and 90°F (10 - 32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

APPLICATION & THINNING: AEROSOL

Shake aerosol vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum for technical support. A test spray on cardboard is recommended to obtain feel for the spray pattern. Hold the aerosol 8-18" (20 - 45 centimetre) from the surface and spray in short even strokes. It is recommended to apply a light first coat. Apply a second heavier coat to ensure proper coverage. A thicker film can be achieved by moving the nozzle closer to the surface. Initial spray may have some foaming or bubbling, but will dissipate as the coating dries. For best results, apply 2 coats. Allow to dry 15-30 minutes between coats.

REMARKS

- If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.
- Wipe off tip when finished.
- Clean-up wet paint with xylene or mineral spirits. Properly discard empty container.
- Do not burn or place in home trash compactor.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 13/05/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V. Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T: +31 (0) 165 593 636 F: +31 (0) 165 593 600

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birdey, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147

Rust-Oleum France S.A.S 38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A Kolenbergstraat 23 3545 Zelem Belgium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@rust-oleum.eu

