

RUST-OLEUM®
INDUSTRIAL



LEAKSEAL®

The flexible rubber coating; seals leaks and cracks

- Watertight semi smooth finish
- Can be top-coated with latex or oil-based paints
- For use on metal, aluminum, PVC, concrete, masonry, asphalt roofing materials, etc.
- Overcoatable with various paints

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

BESKRIVELSE

Designed to fill and seal leaks and cracks on metal, aluminium, galvanized metal, PVC, concrete, masonry, asphalt/bituminous roofing materials, vinyl siding, fiberglass, and more.

ANBEFALT BRUK

Designed to fill and seal leaks and cracks on metal, aluminium, galvanized metal, PVC, concrete, masonry, asphalt/bituminous roofing materials, vinyl siding, fiberglass, and more.

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	20 - 30 minutes
Håndterbar:	45 - 60 minutes
Overmalbar:	Apply second layer LeakSeal after 15 - 30 minutes. Top-coated with water-based or oil-based paints after 24 hours.
Herdetid:	24 hours

ANBEFALT TØRRFILMTYKKELSE

65 µm

TEORETISK FORBRUK

0,74 m² per aerosol at 65 µm dry film thickness

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate, size of the leakage and material losses during application.

KLARGJØRING AV OVERFLATE

Remove all dirt and debris from the area to be coated. Wash area with a detergent and water solution, rinse with fresh water, and allow the surface to dry thoroughly. Remove any loose paint or previous coatings with a wire brush or sandpaper. Lightly sand glossy surfaces. Wipe the sanded surface clean when finished. Test previous coated material for compatibility before use.

PÅFØRINGSBETINGELSER

Use outdoors or in a well-ventilated area such as an open garage. Apply when temperature is between 50°F and 90°F (10 - 32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

PÅFØRING & FORTYNNING: AEROSOL

Shake aerosol vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum for technical support. A test spray on cardboard is recommended to obtain feel for the spray pattern. Hold the aerosol 8-18" (20 - 45 centimetre) from the surface and spray in short even strokes. It is recommended to apply a light first coat. Apply a second heavier coat to ensure proper coverage. A thicker film can be achieved by moving the nozzle closer to the surface. Initial spray may have some foaming or bubbling, but will dissipate as the coating dries. For best results, apply 2 coats. Allow to dry 15- 30 minutes between coats.

MERKNADER

- If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.
- Wipe off tip when finished.
- Clean-up wet paint with xylene or mineral spirits. Properly discard empty container.
- Do not burn or place in home trash compactor.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 20/03/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu