

**RUST-OLEUM®**  
INDUSTRIAL



## ND14 CLEANER/DEGREASER

# Concentrated alkaline cleaner and degreaser

- Removes grease, oil, proteins, dirt and other contaminants from coated, mineral and metal substrates
- Concentrated formulation can be diluted 1:20
- Use as additive for high pressure cleaning
- Non-flammable, virtually odour-free
- Can also be applied by brush, mop or broom

KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# ND14 CLEANER/DEGREASER

## ОПИСАНИЕ

Concentrated, alkaline, non-flammable, virtually odour free cleaning and degreasing solution for 100 m<sup>2</sup>/l.

## ПРЕПОРЪЧНА УПОТРЕБА

ND14 Cleaner/Degreaser should be used to remove grease, oil, proteins, dirt and many other surface contaminants from coated, mineral and steel substrates. Apply with an artificial sponge,cloth or stiff nylon brush or broom. Can also be used as an additive for high pressure (steam) cleaning.

## РАЗХОДНА НОРМА

The content of the concentrated 5 litre packaging will allow you to treat a surface of up to 500 m<sup>2</sup>, based on a dilution of 1:20.

## КОНСУМАЦИЯ

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

## НАЧИН НА УПОТРЕБА

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible. ND14 Cleaner/Degreaser can be applied diluted or concentrated with a sponge, cloth, brush or broom. For normal cleaning a 3 - 5% concentration will be sufficient. The product should be diluted with cold water. After use rinse with plenty of fresh water. If a concentration of more than 5% is used, hot water rinsing is absolutely necessary. As a high-pressure(steam)cleaning additive a 2% concentration is recommended. After cleaning, remove any remaining water and allow the surface to dry, as moisture left on the surface or entrapped into pores may cause premature failure of the coating system. Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Temperature of air, substrate and material between 5 and 35°C.

## ЗАБЕЛЕЖКИ

If used on galvanized steel, zinc, aluminum or anodized aluminum rinse the surface excessively.

## ДАННИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС: 92 g/l  
Забележки относно безопасността: Consult Safety Data Sheet and Safety Information printed on the can.

## PH

12

## СРОК НА ГОДНОСТ

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 20/03/2025

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоително в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

Tor Coatings Ltd (Rust-Oleum Industrial)  
Shandon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

Rust-Oleum France S.A.S.  
36, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

N.V. Martin Mathys S.A.  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)