

**RUST-OLEUM®**  
INDUSTRIAL



## ND14 CLEANER/DEGREASER

# Concentrated alkaline cleaner and degreaser

- Removes grease, oil, proteins, dirt and other contaminants from coated, mineral and metal substrates
- Concentrated formulation can be diluted 1:20
- Use as additive for high pressure cleaning
- Non-flammable, virtually odour-free
- Can also be applied by brush, mop or broom

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# ND14 CLEANER/DEGREASER

## BESKRIVELSE

Concentrated, alkaline, non-flammable, virtually odour free cleaning and degreasing solution for 100 m<sup>2</sup>/l.

## ANBEFALT BRUK

ND14 Cleaner/Degreaser should be used to remove grease, oil, proteins, dirt and many other surface contaminants from coated, mineral and steel substrates. Apply with an artificial sponge, cloth or stiff nylon brush or broom. Can also be used as an additive for high pressure (steam) cleaning.

## TEORETISK FORBRUK

The content of the concentrated 5 litre packaging will allow you to treat a surface of up to 500 m<sup>2</sup>, based on a dilution of 1:20.

## PRAKTISK FORBRUK

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

## BRUKSANVISNING

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible. ND14 Cleaner/Degreaser can be applied diluted or concentrated with a sponge, cloth, brush or broom. For normal cleaning a 3 - 5% concentration will be sufficient. The product should be diluted with cold water. After use rinse with plenty of fresh water. If a concentration of more than 5% is used, hot water rinsing is absolutely necessary. As a high-pressure(steam)cleaning additive a 2% concentration is recommended. After cleaning, remove any remaining water and allow the surface to dry, as moisture left on the surface or entrapped into pores may cause premature failure of the coating system. Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

## PÅFØRINGSBETINGELSER

Temperature of air, substrate and material between 5 and 35°C.

## MERKNADER

If used on galvanized steel, zinc, aluminum or anodized aluminum rinse the surface excessively.

## SIKKERHETSDATA

VOC nivå: 92 g/l  
Merknader angående sikkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

## PH

12

## HOLDBARHET

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 20/03/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)