



ND14 CLEANER/DEGREASER

Concentrated alkaline cleaner and degreaser

- Removes grease, oil, proteins, dirt and other contaminants from coated, mineral and metal substrates
- Concentrated formulation can be diluted 1:20
- Use as additive for high pressure cleaning
- · Non-flammable, virtually odour-free
- · Can also be applied by brush, mop or broom

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

ND14 CLEANER/DEGREASER

DESCRIPTION

Concentrated, alkaline, non-flammable, virtually odour free cleaning and degreasing solution for 100 $\,\mathrm{m^2/l.}$

ODPORÚČANÉ POUŽITIE

ND14 Cleaner/Degreaser should be used to remove grease, oil, proteins, dirt and many other surface contaminants from coated, mineral and steel substrates. Apply with an artificial sponge, cloth or stiff nylon brush or broom. Can also be used as an additive for high pressure (steam) cleaning.

TEORETICKÁ SPOTREBA

The content of the concentrated 5 litre packaging will allow you to treat a surface of up to 500 m², based on a dilution of 1:20.

PRAKTICKÁ VÝDATNOSŤ

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

NÁVOD NA POUŽITIE

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible. ND14 Cleaner/Degreaser can be applied diluted or concentrated with a sponge, cloth, brush or broom. For normal cleaning a 3 - 5% concentration will be sufficient. The product should be diluted with cold water. After use rinse with plenty of fresh water. If a concentration of more than 5% is used, hot water rinsing is absolutely necessary. As a high-pressure(steam)cleaning additive a 2% concentration is recommended. After cleaning, remove any remaining water and allow the surface to dry, as moisture left on the surface or entrapped into pores may cause premature failure of the coating system. Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

PODMIENKY APLIKÁCIE

Temperature of air, substrate and material between 5 and 35°C.

POZNÁMKY

If used on galvanized steel, zinc, aluminum or anodized aluminum rinse the surface excessively.

SAFETY DATA

Úroveň VOC: 92 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information

printed on the can.

PH

12

SKLADOVATEĽNOSŤ

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 20/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T:+31 (0) 165 593 636 F:+31 (0) 165 593 600 Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147

38, av. du Gros Chêne 95322 Herblay France T:+33(0) 130 40 00 44 F:+33(0) 130 40 99 80 N.V. Martin Mathys S.A Kolenbergstraat 23 3545 Zelem Belgium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@rust-pleum eu