



Quality Paints since 1845
MATHYS®



PARACEM® DECO ULTRA CLEAN

Washable interior wall paint with a matt finish

- Excellent cleanability
- Excellent mechanical resistance against rubbing
- Low dirt pick up
- Easy to apply
- Excellent flow

PARACEM® DECO ULTRA CLEAN

DESCRIPTION

Paracem® Deco Ultra Clean is a washable waterborne acrylic interior wall paint with a matt finish. This decorative paint is available in white and in almost every colour, from light to dark tints.

RECOMMENDED USE

Ideal finish for the walls of interior rooms that require regular cleaning (e.g. children's rooms, kitchens,...). Suitable for use on most substrates (plaster, bricks, concrete, etc.) in private and in public buildings.

TECHNICAL DATA

Density (g/cm ³):	1,36 - 1,40 (white - wit - blanc)
Gloss Level:	Matt
Gloss level at 60°:	Matt: 1-2%
Gloss level at 85°:	Matt: 2,5-3,5%
Solids Content in weight:	60,5 - 62,5% (white)
Solids content in volume:	49 - 51% (white)

DRY TIMES BY 20° C/RH 50%

Touch dry:	30 minutes
Dry to recoat:	1 hour
Fully cured:	7 days

RECOMMENDED WET FILM THICKNESS

100 µm

RECOMMENDED DRY FILM THICKNESS

50 µm

THEORETICAL CONSUMPTION

7 - 10 m²/l per coat

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The surface must be dry and free of dust and grease.

You can paint Paracem® Deco Ultra Clean directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous.

You must treat porous surfaces with Paracem® Deco Primer first.

Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first.

Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus).

Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123.

On glass fibre, apply preferably first a coat of Paracem® Deco Primer or Zinsser primers Bulls Eye 123 or 123 Plus before finishing with 2 coats of Paracem® Deco Ultra Clean.

When working in combination with a joint sealant, we recommend using our acrylic sealant Elastopro, which can be painted over after drying for at least 1 hour (20°C, 60% r.h.).

DIRECTIONS FOR USE

To ensure homogeneity, thoroughly stir prior to use. Apply two layers of Paracem Deco Ultra Clean. For best result use a brush with synthetic bristles or a 10 mm micro fiber roller.

APPLICATION CONDITIONS

> 5°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

Apply undiluted with brush with synthetic bristles.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 013 - 019 / Pressure: 160 - 200 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

not recommended.

CLEANING OF EQUIPMENT / SPILLS

Clean tools with water, dispose of residue in the appropriate manner.

REMARKS

Cleaning instructions: Remove the contamination as soon as possible. Most contamination can easily be removed with a soft, damp cloth. Use lukewarm water and a mild colourless detergent. Do not use abrasive cleaning products. Do not use excessive pressure when cleaning as this may result in removing paint which will leave marks.

For more serious contaminations first wipe the substrate with a soft damp cloth, then use Mathys Multi-cleaner (diluted 1:100). Allow to dry.

The best cleaning results are achieved after the Paracem® Deco Ultra Clean has dried for minimum 7 days.

Although extensive evaluations have been undertaken to ensure the cleanability of the Paracem® Deco Ultra Clean it might be possible that some contamination is difficult to remove and leaves traces.

Touching the paint may leave marks this is due to the matt nature of the product (the marks will be more visible on dark colours).

SAFETY DATA

VOC level:	15 g/l
VOC readymix:	15 g/l
VOC category:	A/a
VOC limit:	30 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHelf LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu