



PARASIL

A high build matt silanized wall paint

- Mineral-like matt aspect
- Durable
- Low odour
- Dirt and water repellent
- Low stress

PARASIL

DESCRIPTION

ParaSil® is a high build matt silanized wall paint. Based on siloxane resins and 100% acrylic resins. Suitable for uneven, structured substrates.

RECOMMENDED USE

Mineral matt finish for exterior walls. Can be applied on most mineral substrates and old dispersion paints. Suitable for uneven structured substrates. No cracking in deeper areas of the treated substrate (e.g. brick).

TECHNICAL DATA

Density (g/cm ³):	1,47 - 1,51 (wit)
Gloss Level:	Matt
Solids Content in weight:	68,5 - 70,5 % (wit)
Solids content in volume:	52,5 - 54,5 % (wit)

DRY TIMES BY 20° C/RH 50%

Touch dry:	2-3 hours
Dry to recoat:	12 hours
Fully cured:	1 day

THEORETICAL CONSUMPTION

5 - 7 m²/l per coat

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

SURFACE PREPARATION

Old cleaned layers in good condition and light porous substrates (such as concrete, cement, plaster, etc.) can be recoated directly with ParaSil. Stongly porous substrates and smooth plaster must first be impregnated with a coat of Pegafix Color EXT.

DIRECTIONS FOR USE

Substrate must be sufficiently dry and stable, and well cleaned. Previously cleaned old coatings in good condition and slightly porous and homogeneous substrates can be directly coated with Parasil or with high filling undercoat Parasil Compact in case of uneven surfer. Very porous substrates or smooth renderings or water resistant plasters will be previously impregnated with Pegaprim Exterior. To block stains, graffiti and/or very fast recoating on any substrate, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain.

APPLICATION CONDITIONS

> 10°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

Do not dilute.

APPLICATION & THINNING: ROLLER

Do not dilute.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 013 - 019 / Pressure: 160 - 200 bar.

CLEANING OF EQUIPMENT / SPILLS

Water.

SAFETY DATA

VOC level:	23 g/l
VOC readymix:	23 g/l
VOC category:	IIA/c
VOC limit:	40 g/l
Remarks regarding safety:	Consult safety data sheet and Safety information printed on the can.

SHELF LIFE

At least 1 year from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 7° and 30°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu