

**RUST-OLEUM®**  
INDUSTRIAL



**PEGACRETE®**

## Water-based cementitious repair

- Stronger than concrete
- Easy to apply: just add water and stir
- Can be recoated with all paint types
- Low odour
- For indoor and outdoor use



KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# PEGACRETE®

## DESCRIPTION

Powdered repair product for leveling and repairing cracks, holes and other damages in concrete, cement renderings and non-painted brickwork.

## DOPORUČENÉ POUŽITÍ

For indoor and outdoor works, for levelling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

## TECHNICAL DATA

Hustota (g/cm<sup>3</sup>): 1,6  
Pevnost v tlaku: 38 MN/m<sup>2</sup>  
Pevnost v tahu: 38 MN/m<sup>2</sup>  
Míchací poměr: Pegacrete : Water = 5kg : 1L

## DRY TIMES BY 20° C/RH 50%

Suchý nátěr: 2 days  
Plně vytvrzené: 1 month

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

2 cm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

2 cm

## TEORETICKÁ SPOTŘEBA

Maximum 32 kg/m<sup>2</sup> per layer at 2 cm thickness.

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

On bare substrate: clean with steel brush or sand blaster. The substrate must be solid and free from dust, oil and grease. Porous substrates must be moistened first. Metal parts are to be treated with NOXYDE.

## NÁVOD K POUŽITÍ

Add Pegacrete progressively to water and mix steadily.

## PODMÍNKY POUŽITÍ

Apply at a temperature of minimum 5°C.

## APLIKACE A ŘEDĚNÍ: HRÁBĚ/HADICE

Filling blade or trowel.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water

## POZNÁMKY

Do not use more water than necessary for the application. Pegacrete must be applied with a coat thicknesses of 5-20 mm. For thicker coats (20 mm and more) it is preferable to add some sand to the mortar in the following proportion: for 1 litre of mortar, 0,3 till 0,5 litre of sand 0-4 mm.

## SAFETY DATA

Úroveň těkavých organických

látek: 0 g/l

Grenelle: C

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 20/03/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chiène  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu