



## **PEGACRETE®**

# Water-based cementitous repair

- Stronger than concrete
- Easy to apply: just add water and stir
- · Can be recoated with all paint types
- · Low odour
- · For indoor and outdoor use

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

### **PEGACRETE®**

#### DESCRIPTION

Powdered repair product for leveling and repairing cracks, holes and other damages in concrete, cement renderings and non-painted brickwork.

#### RECOMMENDED USE

For indoor and outdoor works, for levelling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

#### **TECHNICAL DATA**

Density (g/cm³): 1,6
Compressive Strength: 38 MN/m²
Tensile Strength: 38 MN/m²

Mixing Ratio: Pegacrete: Water = 5kg: 1L

#### DRY TIMES BY 20° C/RH 50%

Dry to recoat: 2 days
Fully cured: 1 month

#### RECOMMENDED WET FILM THICKNESS

2 cm

#### RECOMMENDED DRY FILM THICKNESS

2 cm

#### THEORETICAL CONSUMPTION

Maximum 32 kg/m² per layer at 2 cm thickness

#### PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

#### **SURFACE PREPARATION**

On bare substrate: clean with steel brush or sand blaster. The substrate must be solid and free from dust, oil and grease. Porous substrates must be moistened first. Metal parts are to be treated with NOXYDE.

#### **DIRECTIONS FOR USE**

Add Pegacrete progressively to water and mix steadily.

#### **APPLICATION CONDITIONS**

Apply at a temperature of minimum 5°C.

#### **APPLICATION & THINNING: RAKE/TROWEL**

Filling blade or trowel.

#### **CLEANING OF EQUIPMENT / SPILLS**

Water

#### REMARKS

Do not use more water than necessary for the application. Pegacrete must be applied with a coat thicknesses of 5-20 mm. For thicker coats (20 mm and more) it is preferable to add some sand to the mortar in the following proportion: for 1 litre of mortar, 0,3 till 0,5 litre of sand 0-4 mm.

#### **SAFETY DATA**

VOC level: 0 g/l Grenelle: C

Remarks regarding safety: Consult Safety Data Sheet and Safety Information

printed on the can.

#### **SHELF LIFE**

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Date issued:** 20/03/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V. Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T:+31 (0) 165 593 636 F:+31 (0) 165 593 600

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147

Rust-Oleum France S.A.S. 38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem Belglium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@rust-oleum.eu

