



PEGAFLEX®

Levelling filler based on acrylic resins dispersed in water

- · High flexibility and elasticity
- · Excellent adhesion on all sound substrates and paints
- Perfect alkali resistant
- Not affected by ageing thus keeping its original flexibility
- · Sufficiently hard, but can still be sanded easily

PEGAFLEX®

DESCRIPTION

Levelling filler based on acrylic resins dispersed in water.

RECOMMENDED USE

For indoor and outdoor works; can be used on any non-powdering substrates.

TECHNICAL DATA

Density (g/cm 3): \pm 1,8 Gloss Level: Matt Gloss level at 60 $^\circ$: Matt: 3% Solids Content in weight: 78 - 80 % Solids content in volume: 61 - 64 %

DRY TIMES BY 20° C/RH 50%

Touch dry: 3 hours
Dry to handle: 8 hours
Dry to recoat: 24 hours
Fully cured: 2 days

RECOMMENDED WET FILM THICKNESS

1000 µm

RECOMMENDED DRY FILM THICKNESS

630 µm

THEORETICAL CONSUMPTION

Max. 1,8 kg/m² (= 1 mm thick)

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Fill up deep holes with a filler or with a repair mortar (Pegacrete).

Chalking substrates must be primed with Fixonal.

Porous mineral substrates have to be pre-treated with Pegafix.

Bare wood should be impregnated with Adex first.

If you want to recoat with an acrylic paint, you should isolate the filled up parts with Porisol first. If it is necessary to get a thick layer, you should apply several layers after hardening of the previous layer.

DIRECTIONS FOR USE

Use a filling knife and apply thin layers.

APPLICATION CONDITIONS

> 5°C, < 80% R.H.

CLEANING OF EQUIPMENT / SPILLS

With water as long as Pegaflex has not dried; when dry clean with Thinner 22.

REMARKS

Pegaflex can easily be sanded wet, but not dry.

SAFETY DATA

 VOC level:
 30 g/l

 VOC readymix:
 30 g/l

 VOC category:
 A/i

 VOC limit:
 140 g/l

Remarks regarding safety: Consult Safety Data Sheet and Safety Information

printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

ust-Oleum Netherlands B.V

Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T:+31 (0) 165 593 636 F:+31 (0) 165 593 600 Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street

DH3 2RE United Kingdom T: +44 (0)1914 113 146 F: +44 (0)1914 113 147 info@rust-oleum.eu Rust-Oleum France S.A.S. 38, av. du Gros Chêne 95322 Herblay

France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 info@rust-oleum.eu N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem

3545 Zelem Belgium T:+32 (0) 13 460 200 F:+32 (0) 13 460 201 info@rust-oleum.eu