

RUST-OLEUM®
INDUSTRIAL



NOXYDE® PEGANOX



Single pack water-based elastic coating

- Good corrosion protection and waterproofing
- Smooth aesthetic satin finish
- 200% elastic coat does not crack or peel
- Excellent flow, ideal for roller/brush application
- Primer and topcoat in one

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

NOXYDE® PEGANOX

BESKRIVNING

Single pack water-based elastic coating, optimized for brush or roller application.

REKOMMENDERAD ANVÄNDNING

Anticorrosive protection on ferrous and non-ferrous metals.

TEKNISK DATA

Densitet:	1,2
Glansnivå:	Satin
Korrosionsklass:	C4 hög korrosion
Torrsubstansvikt:	58%
Torrsubstansvolym:	48%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 hour
Hanteringstorr:	2 hours
Torktid:	6 hours
Fullt härdad:	2 days

REKOMMENDERAD VÅTFILMSTJOCKLEK

165 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

80 µm

ÅTGÅNG

2 coats of minimum 200 g/m² (5 m²/kg)

ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FÖRBEREDELSE

Apply the usual derusting procedures (min. Sa 2 sand blasting, min. St 2 steel brush, etc.) or by high-pressure water (min. 600 bars). Dedust well after sand blasting.

APPLICERING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Temperature between 8 and 55°C. Air humidity max. 80% R.H. The substrate temperature must be at least 5°C above dew point.

REDSKAP

Apply undiluted.

APPLICERING OCH SPÄDNING: ROLLER

Apply undiluted.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Nozzle: 11 - 13 / Pressure: 220 bars.

Diluted with maximum 3% volume of water.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Apply undiluted.

RENGÖRING AV REDSKAP/SPILL

Water

INFORMATION

When used inside, provide for adequate ventilation.

During work stoppage, fully immerse brush or nozzle in water, empty and clean the tubes.

On non-ferrous substrates, use PVDF Primer or Pegalink as adhesion primer first.

For any information regarding options of guarantee with this system, please contact Technical Service.

SÄKERHETSDATA

VOC-nivå:	15 g/l
VOC färdigmix:	15 g/l
VOC-kategori:	A/i
VOC-gräns:	140 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 13/05/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu