



# **PEGAPRIM® ISOFIX**

# **Super adhesion and stain block primer**

- · Very fast drying
- · Closed, good adhering paint film
- Masks odours
- · Recoatable with most water and solvent borne decorative paints
- · Can be applied at freezing temperatures

# **PEGAPRIM® ISOFIX**

#### DESCRIPTION

Ultra insulating and fast drying universal adhesion primer based on solvent borne Shellacresins

#### RECOMMENDED USE

#### INTERIOR AND EXTERIOR.

Adhesion on metal (copper, bronze, stainless steel) and on smooth hard surfaces (old paint layers, Formica). Exterior uses of Pegaprim Isofix are strictly and exclusively limited for spot priming application as a sealer.

#### **TECHNICAL DATA**

± 1.2 Density (g/cm3): Gloss Level: Satin Gloss level at 60°: Satin: ± 10% Solids Content in weight: ± 54 % Solids content in volume: ± 30 %

#### DRY TIMES BY 20° C/RH 50%

Touch dry: 15 minutes Dry to recoat: 45 minutes Fully cured: 1 day

#### RECOMMENDED WET FILM THICKNESS

100 µm

#### RECOMMENDED DRY FILM THICKNESS

30 µm

#### THEORETICAL CONSUMPTION

 $\pm 10 \text{ m}^2/\text{I}$ 

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### SURFACE PREPARATION

The substrate should be clean, dry and stable. If necessary, degrease. Contamination has to be removed as thoroughly as possible. Strongly solvent borne topcoats must be tested for their tolerance first (e.g. polyurethane, epoxy).

#### **DIRECTIONS FOR USE**

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

# APPLICATION CONDITIONS

> -1°C. < 80% R.H.

# **APPLICATION & THINNING: ROLLER**

Apply undiluted.

#### **APPLICATION & THINNING: AIRLESS SPRAY**

Nozzle: 0,015 inch / Pressure: 150 - 200 bars

## **APPLICATION & THINNING: AIR-ATOMISED SPRAY**

Dilute with ± 2% volume denaturised alcohol.

#### **CLEANING OF EQUIPMENT / SPILLS**

Denaturised alcohol.

#### REMARKS

In case of too fast evaporation or spraying, add  $\pm\,2\%$  volume denaturised alcohol.

#### **SAFETY DATA**

VOC level: 480 g/l VOC readvmix: 500 g/l VOC category: A/i 500 g/l VOC limit:

Consult Safety Data Sheet and Safety Information Remarks regarding safety:

printed on the can.

#### **SHELF LIFE**

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T: +31 (0) 165 593 636 F: +31 (0) 165 593 600

Tor Coatings Ltd (Rust-Oleum Inc Shadon Way, Portobello Ind. Estate Birtley, Chester-le-Street

DH3 2RE United Kingdon : +44 (0)1914 113 146 +44 (0)1914 113 147 Rust-Oleum France S.A.S. 38, av. du Gros Chêne 95322 Herblay

France : +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem

Belgium T : +32 (0) 13 460 200 F: +32 (0) 13 460 201