



PEGAPRIM[®] SANITOP

Protection of the dry film against fungal degradation

- Primer and topcoat in one
- Protection of the dry film against fungal degradation
- For inner and outer use
- High quality satin mat finish
- Excellent adhesionIdeal for damp areas

PEGAPRIM® SANITOP

DESCRIPTION

Wall paint based on water-based acrylic resins. Primer and topcoat in one. Protection of the dry film against fungal degradation. Ideal for damp areas.

RECOMMENDED USE

For the interior coating of humid sensitive areas. As a durable interior / exterior coating on mineral substrates (masonry, plaster, concrete, bricks) with enhanced protection of the dried coat against fungal degradation.

TECHNICAL DATA

Density (g/cm ³):	± 1,4
Gloss Level:	Semi-Matt
Gloss level at 60°:	Satin Matt: ± 5%
Solids Content in weight:	62 - 65 %
Solids content in volume:	47 - 50 %

DRY TIMES BY 20° C/RH 50%

Touch dry:	40 minutes
Dry to recoat:	4 hours
Fully cured:	1 day

RECOMMENDED WET FILM THICKNESS

125 µm

RECOMMENDED DRY FILM THICKNESS

60 µm

THEORETICAL CONSUMPTION

7 - 10 m²/l per coat

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The substrate must be sufficiently dry and stable; clean thoroughly.

On porous substrates apply first a coat of diluted Pegaprim Xpress, or preferably a coat of Pegafix.

On smooth bricks, apply a first coat of Pegaprim Xpress.

Impregnate old chalking paints after cleaning, with a coat of Fixonal or Pegafix.

Fill up holes and seal joints or fissures with Elastofill. If necessary, equalise with Pegaflex.

Flat down and remove dust. Hereafter, apply 1 - 2 coats of Pegaprim Sanitop.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

> 5°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

Apply with flat brush.

APPLICATION & THINNING: ROLLER

Apply with dispersion roller.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 013 - 018 / Pressure: 180 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Dilute with water (3 - 5% volume).

CLEANING OF EQUIPMENT / SPILLS

Water.

REMARKS

Thinning:

- For outside use: do not dilute.
- For inside use: dilute with 5 to 10% volume of water or even better with 5% volume of Fair-Décor.

SAFETY DATA

VOC level:	23 g/l
VOC readymix:	23 g/l
VOC category:	A/i
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu