


RUST-OLEUM®
INDUSTRIAL



NOXYDE® PEGARUST

Single pack solvent-based flexible anti-corrosion coating



- Ultimate corrosion protection, even in low temperatures or damp surfaces
- Protects against cracking and peeling
- UV- and impact-resistant
- Primer and topcoat in one
- Excellent resistance against chemical agents in the atmosphere

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

NOXYDE® PEGARUST

DESCRIPTION

Single pack solvent-based elastic coating for application at low temperatures and damp conditions.

DOPORUČENÉ POUŽITÍ

On iron, galvanised steel, aluminium, zinc, etc.

TECHNICAL DATA

Hustota (g/cm ³):	1,15
Úroveň lesku:	Semi-Matt
Obsah pevných látek v hmotnosti:	55%
Obsah pevných látek v objemu:	46%

DRY TIMES BY 20° C/RH 50%

Suchý nátěr:	24 - 48 hours
Plně vytvrzené:	1 week

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

345 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

160 µm

TEORETICKÁ SPOTŘEBA

± 2,9 m²/l per coat (it is recommended to apply 2 coats)

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

Degrease if necessary. Derust substrate according to the conventional derusting techniques (sandblasting Sa2 and mechanical sanding St3). On a humid substrate, apply the first coat by brush or roller.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

May be applied in humid weather conditions. Minimum ambient temperature: -5°C.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply undiluted.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 015 / Pressure: 200 - 220 bars. Apply undiluted.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not advisable.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Thinner 22

POZNÁMKY

On new galvanised surfaces and new zinc apply first a coat of Metal Cladding Primer or PVDF Primer.

For any information regarding options of guarantee with this system, please contact Technical Service.

SAFETY DATA

Úroveň těkavých organických látek:	500 g/l
VOC readymix:	500 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 20/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu