


**RUST-OLEUM®**  
INDUSTRIAL



## NOXYDE® PEGARUST

# Single pack solvent-based flexible anti-corrosion coating



- Ultimate corrosion protection, even in low temperatures or damp surfaces
- Protects against cracking and peeling
- UV- and impact-resistant
- Primer and topcoat in one
- Excellent resistance against chemical agents in the atmosphere

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# NOXYDE® PEGARUST

## DESCRIPTION

Single pack solvent-based elastic coating for application at low temperatures and damp conditions.

## ODPORÚČANÉ POUŽITIE

On iron, galvanised steel, aluminium, zinc, etc.

## TECHNICAL\_DATA

Hustota (g/cm <sup>3</sup> ):	1,15
Úroveň lesku:	Semi-Matt
Obsah pevných látok v hmotnosti:	55%
Obsah pevných látok v objeme:	46%

## DRY TIMES BY 20° C/RH 50%

Suchý na opätovné natieranie:	24 - 48 hours
Úplne vytvrdnuté:	1 week

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

345 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

160 µm

## TEORETICKÁ SPOTREBA

± 2,9 m<sup>2</sup>/l per coat (it is recommended to apply 2 coats)

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

Degrease if necessary. Derust substrate according to the conventional derusting techniques (sandblasting Sa2 and mechanical sanding St3). On a humid substrate, apply the first coat by brush or roller.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

May be applied in humid weather conditions. Minimum ambient temperature: -5°C.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted.

## APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 015 / Pressure: 200 - 220 bars. Apply undiluted.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not advisable.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Thinner 22

## POZNÁMKY

On new galvanised surfaces and new zinc apply first a coat of Metal Cladding Primer or PVDF Primer.

For any information regarding options of guarantee with this system, please contact Technical Service.

## SAFETY DATA

Úroveň VOC:	500 g/l
VOC readymix:	500 g/l
Kategória VOC:	A/i
Limit VOC:	500 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 20/03/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chiène  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu