

**RUST-OLEUM®**  
INDUSTRIAL



## PEGASOL® QUARTZ

# Durable anti-slip coating.

- Durable Quartz finish
- Easy application
- Fast drying
- Abrasion resistant
- Odourless

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# PEGASOL® QUARTZ

## DESCRIPTION

Two-pack water based anti-slip floor coating for indoor and outdoor application.

## DOPORUČENÉ POUŽITÍ

For external works: on balconies, terraces, etc. For inside works: on industrial floors, warehouses, (in garages, a top coat in Pegakote has to be applied on Pegasol Quartz).

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,6
Úroveň lesku:	Satin
Obsah pevných látek v hmotnosti:	77%
Obsah pevných látek v objemu:	63%
Míchací poměr:	Base : Activator = 7 : 0.5 (Weight)

## DRY TIMES BY 20° C/RH 50%

Dotykem suché:	45 minutes
Suché na manipulaci:	2 hours
Suchý nátěr:	6 hours
Plně vytvrzené:	1 week
Život v hrci:	1 hour (12 hours when diluted with 5% volume water)

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

500 µm (800 g/m<sup>2</sup>)

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

315 µm

## TEORETICKÁ SPOTŘEBA

800 g/m<sup>2</sup> per coat

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

The substrate should be clean, dry and free from rising ground water. Pegasol Quartz can be applied directly on tiles, ceramics (even glazed), non-porous natural stones, tarmacadam. Porous concrete must be impregnated first with Primer 44 HS or with Vernac diluted with 10% volume Thinner 22. Curing compounds in case of poly concrete have to be removed by sand or grit blasting. On new or non-porous concrete, remove the cement grout by sand or grit blasting or attack with diluted hydrochloric acid (3 l hydrochloric acid in 10 l water, let it act for 10 minutes and rinse abundantly with clear water), let it dry a few days before application.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Minimum 8°C, maximum 80% R.H.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted by preference.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply undiluted by preference.

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Not recommended.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water

## POZNÁMKY

- Pegasol Quartz will withstand foot traffic after 6 hours and wheeled traffic after 3 days
- Because of the development of acid products in Pegasol (Quartz) under influence of UV-rays, it should not be finished with polyurethane-varnishes (e.g. Pegagraff Hydro) in case of external works
- Add the hardener to the base gradually with good mechanical stirring
- When Pegasol Quartz has to be recoated, please contact our Technical Service
- For applications on balconies and terraces, please contact our Technical Service.

## SAFETY DATA

Úroveň těkavých organických

látek: 30 g/l

VOC readymix: 30 g/l

Kategorie VOC: A/j

Limitní hodnota VOC: 140 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 20/03/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu