

RUST-OLEUM®
INDUSTRIAL



PEGASOL® QUARTZ

Durable anti-slip coating.

- Durable Quartz finish
- Easy application
- Fast drying
- Abrasion resistant
- Odourless

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

PEGASOL® QUARTZ

DESCRIPTION

Two-pack water based anti-slip floor coating for indoor and outdoor application.

ODPORÚČANÉ POUŽITIE

For external works: on balconies, terraces, etc. For inside works: on industrial floors, warehouses, (in garages, a top coat in Pegakote has to be applied on Pegasol Quartz).

TECHNICAL DATA

Hustota (g/cm ³):	1,6
Úroveň lesku:	Satin
Obsah pevných látok v hmotnosti:	77%
Obsah pevných látok v objeme:	63%
Pomer miešania:	Base : Activator = 7 : 0.5 (Weight)

DRY TIMES BY 20° C/RH 50%

Na dotyk suché:	45 minutes
Suché na manipuláciu:	2 hours
Suchý na opätovné natieranie:	6 hours
Úplne vytvrdnuté:	1 week
Život v hmci:	1 hour (12 hours when diluted with 5% volume water)

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

500 µm (800 g/m²)

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

315 µm

TEORETICKÁ SPOTREBA

800 g/m² per coat

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

The substrate should be clean, dry and free from rising ground water. Pegasol Quartz can be applied directly on tiles, ceramics (even glazed), non-porous natural stones, tarmacadam. Porous concrete must be impregnated first with Primer 44 HS or with Vernac diluted with 10% volume Thinner 22. Curing compounds in case of poly concrete have to be removed by sand or grit blasting. On new or non-porous concrete, remove the cement grout by sand or grit blasting or attack with diluted hydrochloric acid (3 l hydrochloric acid in 10 l water, let it act for 10 minutes and rinse abundantly with clear water), let it dry a few days before application.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Minimum 8°C, maximum 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted by preference.

APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted by preference.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Not recommended.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not recommended.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water

POZNÁMKY

- Pegasol Quartz will withstand foot traffic after 6 hours and wheeled traffic after 3 days
- Because of the development of acid products in Pegasol (Quartz) under influence of UV-rays, it should not be finished with polyurethane-varnishes (e.g. Pegagraff Hydro) in case of external works
- Add the hardener to the base gradually with good mechanical stirring
- When Pegasol Quartz has to be recoated, please contact our Technical Service
- For applications on balconies and terraces, please contact our Technical Service.

SAFETY DATA

Úroveň VOC:	30 g/l
VOC readymix:	30 g/l
Kategória VOC:	A/j
Limit VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 20/03/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu