

**RUST-OLEUM®**  
INDUSTRIAL



## PEGASOL® QUARTZ

# Durable anti-slip coating.

- Durable Quartz finish
- Easy application
- Fast drying
- Abrasion resistant
- Odourless

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# PEGASOL® QUARTZ

## BESKRIVNING

Two-pack water based anti-slip floor coating for indoor and outdoor application.

## REKOMMENDERAD ANVÄNDNING

For external works: on balconies, terraces, etc. For inside works: on industrial floors, warehouses, (in garages, a top coat in Pegakote has to be applied on Pegasol Quartz).

## TEKNISK DATA

Densitet:	1,6
Glansnivå:	Satin
Torrsubstansvikt:	77%
Torrsubstansvolym:	63%
Blandningsförhållande:	Base : Activator = 7 : 0.5 (Weight)

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	45 minutes
Hanteringstorr:	2 hours
Torktid:	6 hours
Fullt härdad:	1 week
Brukstid:	1 hour (12 hours when diluted with 5% volume water)

## REKOMMENDERAD VÅTFILMSTJOCKLEK

500 µm (800 g/m<sup>2</sup>)

## REKOMMENDERAD TORRFILMSTJOCKLEK

315 µm

## ÅTGÅNG

800 g/m<sup>2</sup> per coat

## ÅTGÅNG INFORMATION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FÖRBEREDELSE

The substrate should be clean, dry and free from rising ground water. Pegasol Quartz can be applied directly on tiles, ceramics (even glazed), non-porous natural stones, tarmacadam. Porous concrete must be impregnated first with Primer 44 HS or with Vernac diluted with 10% volume Thinner 22. Curing compounds in case of poly concrete have to be removed by sand or grit blasting. On new or non-porous concrete, remove the cement grout by sand or grit blasting or attack with diluted hydrochloric acid (3 l hydrochloric acid in 10 l water, let it act for 10 minutes and rinse abundantly with clear water), let it dry a few days before application.

## APPLICERING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICERINGSFÖRHÅLLANDEN

Minimum 8°C, maximum 80% R.H.

## APPLICERING OCH SPÄDNING: PENSEL

Apply undiluted by preference.

## APPLICERING OCH SPÄDNING: ROLLER

Apply undiluted by preference.

## APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Not recommended.

## APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Not recommended.

## RENGÖRING AV REDSKAP/SPILL

Water

## INFORMATION

- Pegasol Quartz will withstand foot traffic after 6 hours and wheeled traffic after 3 days
- Because of the development of acid products in Pegasol (Quartz) under influence of UV-rays, it should not be finished with polyurethane-varnishes (e.g. Pegagraff Hydro) in case of external works
- Add the hardener to the base gradually with good mechanical stirring
- When Pegasol Quartz has to be recoated, please contact our Technical Service
- For applications on balconies and terraces, please contact our Technical Service.

## SÄKERHETSDATA

VOC-nivå:	30 g/l
VOC färdigmix:	30 g/l
VOC-kategori:	A/j
VOC-gräns:	140 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 20/03/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)