

Quality Paints since 1845
MATHYS[®]



PLASTOPAN SUPER N

Solvent-based synthetic filler

- Quick hardening
- Excellent filling
- Contains no water soluble substances
- absorbs very little of the applied paint

PLASTOPAN SUPER N

DESCRIPTION

Solvent-based synthetic filler based on linseed oil alkyd resin.

RECOMMENDED USE

Smoothing out uneven areas in indoor and outdoor woodwork that have to be recoated with oil based or synthetic paints.

TECHNICAL DATA

Density (g/cm ³):	± 2,4
Gloss Level:	Matt
Solids Content in weight:	± 87 %
Solids content in volume:	± 70 %

DRY TIMES BY 20° C/RH 50%

Touch dry:	1 hour
Dry to recoat:	24 hours
Fully cured:	1 week

RECOMMENDED WET FILM THICKNESS

± 2 mm

RECOMMENDED DRY FILM THICKNESS

± 1,4 mm

THEORETICAL CONSUMPTION

1 - 5 kg/m²

PRACTICAL CONSUMPTION

Depends on several factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

SURFACE PREPARATION

Clean the substrate thoroughly, remove old weather-stained paint that is adhering poorly. Apply a thin layer of Fassiprim (diluted with ± 10% volume white spirit) on surfaces before filling them.

First treat substrates that are powdering or chalking with Fixonal. After filling and sanding, apply a primer coat of Fassiprim on all the surfaces; if matt finished portions are still visible after the primer dries, re-apply the primer to obtain a uniform appearance.

DIRECTIONS FOR USE

Apply in a dry and well-ventilated environment.

APPLICATION CONDITIONS

Apply in a dry and well ventilated environment.

CLEANING OF EQUIPMENT / SPILLS

White spirit

REMARKS

Apply thin layers of Plastopan Super N.

SAFETY DATA

VOC level:	390 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the packaging.

SHELF LIFE

Minimum of 2 years from date of production, if stored in the unopened, original packaging in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu