

RUST-OLEUM®
INDUSTRIAL



PRIMER 44HS®

Primer for brittle or weathered roofs, floors, walls

- Excellent fixation for stabilizing loose particles
- Prevents porous substrates from absorbing expensive coatings
- Flexible paint withstands temperature changes
- Quickly water-resistant (1 hour after application at 20 °C)
- Can be used on roofs, floors and walls

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

PRIMER 44HS®

BESKRIVNING

Ready to use single pack binding primer based on chlorinated rubber improves adhesion of coatings on porous mineral surfaces.

REKOMMENDERAD ANVÄNDNING

Fixation layer for porous and unpainted mineral substrates.

TEKNISK DATA

Densitet:	1,1
Glansnivå:	Glans
Torrsubstansvikt:	45%
Torrsubstansvolym:	32%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 hour
Hanteringstorr:	1 hour
Torktid:	24 hours
Fullt härdad:	24 hours

REKOMMENDERAD VÅTFILMSTJOCKLEK

70 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

23 µm

ÅTGÅNG

14 m²/l

ÅTGÅNG INFORMATION

10 - 15 m²/l. Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FÖRBEREDELSE

Clean and degrease the substrate. If the substrate is an acrylic paint, this must NOT be recoated with Primer 44HS (the acrylic paint is affected by the solvents of Primer 44HS). In such a case, replace Primer 44HS with Pegafix.

APPLICERING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APPLICERING OCH SPÄDNING: PENSEL

All types. Do not dilute.

APPLICERING OCH SPÄDNING: ROLLER

All types. Do not dilute.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Do not dilute. Nozzle: 011 - 013. Pressure: 150 - 170 bars.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Do not dilute.

RENGÖRING AV REDSKAP/SPILL

Thinner 22.

INFORMATION

Ready for use. Do not dilute. Reversible paint system, this means that the product dissolves in its own solvent.

SÄKERHETSDATA

VOC-nivå:	599 g/l
VOC färdigmix:	599 g/l
VOC-kategori:	A/h
VOC-gräns:	750 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 20/03/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu